




## **RF & MICROWAVE COMPONENTS**



# **PPI**




**High-Q, Low ESR Multi-Layer Ceramic Capacitors**  
**High-Q High Voltage Custom Assemblies**





## Traditional High Q (>10,000) Low ESR Multi-Layer Ceramic Capacitors

Passive Plus (PPI) specializes in Magnetic & Non-Magnetic HI-Q Components, supplying reliable quality components to the Aerospace, Telecommunications, Medical Semiconductor, and Military industries.



*Marking shown for illustration purposes only.  
Actual marking may differ.*

PPI is an American (New York), Woman owned Business.

- PPI is ISO9001:2015 certified.
- S level reliability
- Mil C 55681
- Mil C 123
- EAR 99 Compliant
- No ITAR Issues
- Export Compliant
- RoHS and REACH Compliant

PPI has been audited by some of the largest and most successful companies in the world and has received extremely high audit ratings. We believe our audit ratings are best in class. PPI is known for Outstanding Customer Service and RF Engineering Support.



# Traditional High Q (>10,000) Low ESR Multi-Layer Ceramic Capacitors

## Product Features

- High Q
- High Power
- Low ESR/ESL
- Low Noise
- High Self-Resonance
- Ultra Stable Performance


## Product Applications

### Typical Functional Applications:

- Tuning • Bypass • Coupling
- Feedback • D.C. Blocking
- Impedance Matching


### Typical Circuit Applications:

- UHF/Microwave RF Power Amplifiers
- Mixers • Oscillators • Filter Networks
- Low Noise Amplifiers • Timing Circuits and Delay Lines




Marking shown for illustration purposes only. Actual marking may differ.

## Part Numbering



## Case Size (Chip) Dimensions

	<b>0505</b>	<b>1111</b>	<b>2225</b>	<b>3838</b>	<b>6040</b>	<b>7676</b>
Length (L <sub>c</sub> )	0.055 + 0.015 to -0.010 (1.40 + 0.38 to -0.25)	0.110 + 0.020 to -0.010 (2.79 + 0.51 to -0.25)	0.225 - 0.010 + 0.25 (5.72 - 0.25 + 0.64)	0.380 - 0.010 + 0.015 (9.65 - 0.25 + 0.38)	0.614 - 0.010 + 0.015 (15.6 - 0.25 + 0.38)	0.760 - 0.010 + 0.015 (19.3 - 0.25 + 0.38)
Width (W <sub>c</sub> )	0.055 ± .010 (1.40 ± 0.25)	0.110 ± 0.010 (2.79 ± 0.25)	0.250 ± 0.015 (6.35 ± 0.38)	0.380 ± 0.010 (9.65 ± 0.25)	0.433 ± 0.010 (11.0 ± 0.25)	0.760 ± 0.010 (19.3 ± 0.25)
Thickness (T <sub>c</sub> )	0.057 (1.45 max)	0.10 (2.54 max)	0.165 (4.19 max)	0.170 (4.32 max)	0.154 ± 0.008 (3.90 ± 0.20) max	0.154 ± 0.008 (3.90 ± 0.20) max
Overlap (B)	0.02 (0.51 max)	0.024 (0.60 max)	0.020 - 0.047 (0.50 - 1.20) max	0.024 - 0.059 (0.60 - 1.50)	0.063 (1.60) max	0.063 (1.60) max





# Traditional High Q (>10,000) Low ESR Multi-Layer Ceramic Capacitors

## ≠ Temperature Coefficient

C: -55°C to 125°C 0±30ppm/°C; >125 °C to 200°C 0±60ppm/°C  
 P: +90±20ppm/°C

## ≠ Rated Capacitance

Capacitance is less than 10pF; for example: 1R0=1.0pF, R denotes decimal point  
 Capacitance greater than 10pF; for example: 101=100pF, the third number is the power of 10

## ≠ Tolerance

Capacitance Tolerance								
Code	A	B	C	D	F	G	J	K
Tolerance	±0.05pF	±0.1pF	±0.25pF	±0.5pF	±1%	±2%	±5%	±10%

## ≠ Termination Types and Codes

Magnetic			⊗ Non-Magnetic ⊗		
Termination Code	Type	Magnetic Termination	Termination Code	Type	Non-Magnetic Terminations
W	Chip	100% Sn Solder over Nickel Plating	P	Chip	100% Sn Solder over Copper Plating
L	Chip	90% Sn10%Pb Tin/Lead Solder over Nickel Plating	MN	Microstrip	Silver-Plated Copper
MS	Microstrip	Silver-Plated Copper	AN	Axial Ribbon	
AR	Axial Ribbon		FN	Radial Ribbon	
RR	Radial Ribbon		RN	Axial Wire	
RW	Axial Wire		BN	Radial Wire	
AW	Radial Wire				



## Traditional High Q (>10,000) Low ESR Multi-Layer Ceramic Capacitors

### ≠ Voltages

Code	Rated Voltage	Code	Rated Voltage
500	50V	152	1500V
101	100V	202	2000V
151	150V	252	2500V
201	200V	302	3000V
301	300V	362	3600V
501	500V	502	5000V
102	1000V	722	7200V

### ≠ Laser Marking

An “X” at the end of the part number indicates the part is marked.


### ≠ Packing Orientation Option

TV: Tape carrier packaging Vertical Orientation.

Vertical orientation means that if the part is lifted from the tape without any rotation and placed on a substrate, its electrodes will be perpendicular to the substrate plane. This impacts the frequency of First Parallel Resonance (suckout).

### ≠ Performance Requirements

Capacitors are designed and manufactured to meet the requirements of MIL-PRF-55681 and MIL-PRF-123.

All products are in compliance with RoHS instruction. 



Traditional High Q (>10,000) Low ESR  
Multi-Layer Ceramic Capacitors

**0505C/P (0.055" x 0.055")**

### ≠ Product Features

- High Q
- High Power
- Low ESR/ESL
- Low Noise
- High Self-Resonance
- Ultra Stable Performance
- Capacitance Range:  
0.1pF to 1000pF
- Working Voltage: 150V
- Extended Voltage: 300V

### ≠ Product Applications

#### Typical Functional Applications:

- Tuning • Bypass • Coupling
- Feedback • D.C. Blocking
- Impedance Matching


#### Typical Circuit Applications:

- UHF/Microwave RF Power Amplifiers
- Mixers • Oscillators • Filter Networks
- Low Noise Amplifiers • Timing Circuits and Delay Lines



Marking shown for illustration purposes only. Actual marking may differ.

### ≠ Part Numbering



### ≠ Capacitance Tolerance Codes

Code	A	B	C	D	F	G	J	K
<b>Tol.</b>	±0.05pF	±0.1pF	±0.25pF	±0.5pF	±1%	±2%	±5%	±10%

### ≠ Voltage Codes

Voltage	Code	Voltage	Code
50V	500	200V	201
100V	101	250V	251
150V	151	300V	301

Please note that the contents of this document are subject to change at any time at PPI's sole discretion. The most up-to-date version of this document is available at [www.passiveplus.com](http://www.passiveplus.com)




Traditional High Q (>10,000) Low ESR  
Multi-Layer Ceramic Capacitors

**0505C/P (0.055" x 0.055")**

**≠ 0505C/P Capacitance Values**

- NP0=C; P90=P
- **Maximum Capacitance: 0505P=100pF; 0505C=1000pF**
- \* - Available in NP0 only.

Special capacitances, tolerances and WVDC are available. Please contact PPI.



Cap. pF	Cap Code	Tol.	Rated WVDC		Cap. pF	Cap Code	Tol.	Rated WVDC		Cap. pF	Cap Code	Tol.	Rated WVDC		Cap. pF	Cap Code	Tol.	Rated WVDC	
			Std.	Ext.				Std.	Ext.				Std.	Ext.				Std.	Ext.
0.1	0R1		150V	250V or 300V	2.4	2R4	A,B,C,D	150V	250V or 300V	20	200	F,G,J,K	150V	250V or 300V	160	161*	F,G,J,K	150V	200V
0.2	0R2				2.7	2R7				22	220				180	181*			
0.3	0R3				3.0	3R0				24	240				200	201*			
0.4	0R4				3.3	3R3				27	270				220	221*			
0.5	0R5				3.6	3R6				30	300				240	241*			
0.6	0R6				3.9	3R9				33	330				270	271*			
0.7	0R7				4.3	4R3				36	360				300	301*			
0.8	0R8				4.7	4R7				39	390				330	331*			
0.9	0R9				5.1	5R1				43	430				360	361*			
1.0	1R0				5.6	5R6				47	470				390	391*			
1.1	1R1	A,B,C,D			6.2	6R2				51	510				430	431*			
1.2	1R2				6.8	6R8				56	560				470	471*			
1.3	1R3				7.5	7R5				62	620				510	511*			
1.4	1R4				8.2	8R2				68	680				560	561*			
1.5	1R5				9.1	9R1				75	750				620	621*			
1.6	1R6		10	100	82	820	750	750	680	681*	F,G,J,K	150V	200V						
1.7	1R7		11	110	91	910	820	820	750	751*									
1.8	1R8		12	120	100	101	910	910	820	821*									
1.9	1R9		13	130	110	111*	100	101	910	911*									
2.0	2R0		15	150	120	121*	110	111*	1000	102*									
2.1	2R1		16	160	130	131*	120	121*											
2.2	2R2		18	180	150	151*	130	131*											


\*Available in NP0 only



Traditional High Q (>10,000) Low ESR  
Multi-Layer Ceramic Capacitors

**0505C/P (0.055" x 0.055")**

## ≠ Termination Types and Codes



Chip Termination:  
Codes: **W, L, P**

Magnetic Terminations	
Termination Code	Termination
<b>W</b>	100% Tin Solder over Nickel Barrier
<b>L</b>	90%Tin/10%Lead Solder over Nickel Barrier
Non-Magnetic Terminations	
Termination Code	Termination
<b>P</b>	100% Tin Solder over Copper Barrier

## ≠ Dimensions Unit: inch (millimeter)

Magnetic Termination						
Code		Length		Width	Thickness	Overlap
		Lc		Wc	Tc	B
W/L	Chip	0.055	+0.015 -0.010	0.055 ± 0.010	0.057 max	0.014 ± 0.006
		(1.40	+0.38 -0.25)	(1.40 ± 0.25)	(1.45 max)	(0.356 ± 0.152)

Non-Magnetic Termination						
Code		Length		Width	Thickness	Overlap
		Lc		Wc	Tc	B
P	Chip	0.055	+0.015 -0.010	0.055 ± 0.010	0.057 max	0.014 ± 0.006
		(1.40	+0.38 -0.25)	(1.40 ± 0.25)	(1.45 max)	(0.356 ± 0.152)

Note: "Non-Magnetic" means no magnetic materials.





Traditional High Q (>10,000) Low ESR  
Multi-Layer Ceramic Capacitors

**0505C/P (0.055" x 0.055")**

### ≠ Electrical Specifications

Quality Factor (Q)	Greater than 10,000 at 1 MHz
Insulation Resistance (IR)	10 <sup>5</sup> MegaOhms min. @ +25°C rated WVDC 10 <sup>4</sup> MegaOhms min. @ +125°C rated WVDC
Rated Voltage	See Rated Voltage in Capacitance Table
Dielectric Withstanding Voltage (DWV)	250% of Rated Voltage of 5 seconds
Operating Temperature Range	-55°C to 200°C
Temperature Coefficient (TC)	<b>C:</b> -55°C to 125°C 0±30ppm/°C; >125°C to 200°C 0±60ppm/°C <b>P:</b> -55°C to 200°C +90±20ppm/°C
Capacitance Drift	±0.02% or ±0.02pF, whichever is greater
Piezoelectric Effects	None
Termination Type	See Termination Type Table

Capacitors are designed and manufactured to meet the requirements of MIL-PRF-55681 and MIL-PRF-123.

### ≠ Environmental Specifications

	Specification	Test Parameters
Thermal Shock	<b>DWV:</b> The initial Value <b>IR:</b> Shall not be less than 30% of the initial value. <b>Capacitance Change:</b>	MIL-STD-202, Method 107, Condition A. At the maximum rated temperature (-55°C and 200°C) stay 30 minutes, the time of removing shall not be more than 3 minutes. Perform five cycles.
Moisture Resistance	No more than 0.5% or 0.5pF, whichever is greater.	MIL-STD-202, Method 106
Humidity (Steady State)	<b>DWV:</b> The initial Value <b>IR:</b> The initial value. <b>Capacitance Change:</b> No more than 0.5% or 0.5pF, whichever is greater.	MIL-STD-202, Method 103, Condition A With 1.5Volts DC applied while subjected to an environment of 85°C with 85% relative humidity for 240 hours minimum.
Life	<b>IR:</b> Shall not be less than 30% of the initial value. <b>Capacitance Change:</b> No more than 2.0% or 0.5pF, whichever is greater.	MIL-STD-202, Method 108. For 2000 hours, at 200°C. Rated Voltage DC applies.
Terminal Strength	<b>Force:</b> 10lbs typical, 5lbs. Minimum. <b>Duration Time:</b> 5 to 10 seconds	MIL-STD-202, Method 211A, Test Condition A. Applied a force and maintained for a period of 5 to 10 seconds. The force shall be in the direction of the axes of the terminations.



Traditional High Q (>10,000) Low ESR  
Multi-Layer Ceramic Capacitors


**0505C/P (0.055" x 0.055")**

## ≠ FPR -- First Parallel Resonance (FPRs)

### ≠ Definitions and Measurement Conditions

The **First Parallel Resonance, FPR**, is defined as the lowest frequency at which a suckout or notch appears in  $|S_{21}|$ .


It is generally independent of substrate thickness or dielectric constant, but does depend on capacitor orientation. A horizontal orientation means the capacitor electrode planes are parallel to the plane of the substrate; a vertical orientation means the electrode planes are perpendicular to the substrate.



## ≠ FSR -- First Series Resonance (FSRs)

### ≠ Definitions and Measurement Conditions

The **First Series Resonance, FSR**, is defined as the lowest frequency at which the imaginary part of the input impedance,  $\text{Im}[Z_{in}]$ , equals zero. Should  $\text{Im}[Z_{in}]$  or the real part of the input impedance,  $\text{Re}[Z_{in}]$ , not be monotonic with frequency at frequencies lower than those at which  $\text{Im}[Z_{in}] = 0$ , the FSR shall be considered as undefined (represented as a gap in the plot). FSR is dependent on internal capacitor structure; substrate thickness and dielectric constant; capacitor orientation, as defined alongside the FPR plot; and mounting pad dimensions.



The measurement conditions are: substrate – Rogers RO4350; substrate dielectric constant = 3.66; horizontal mount substrate thickness (mils) = 25; gap in microstrip trace (mils) = 15; horizontal mount microstrip trace width (mils) = 55. Reference planes at sample edges.

All data has been derived from electrical models created by Modelithics, Inc., a specialty vendor contracted by PPI. The models are derived from measurements on a large number of parts disposed on several different substrates.




Traditional High Q (>10,000) Low ESR  
Multi-Layer Ceramic Capacitors

**0505C/P (0.055" x 0.055")**

### ⚡ ESR vs. Frequency

0505C/P ESR vs Frequency



0505C ESR vs Frequency





Traditional High Q (>10,000) Low ESR  
Multi-Layer Ceramic Capacitors


**0505C/P (0.055" x 0.055")**

### ≠ Q vs. Frequency

0505C/P Q vs Frequency




0505C Q vs Frequency




### ≠ Current Rating vs. Capacitance

0505C/P Current Rating vs Capacitance



0505C Current Rating vs Capacitance




Current limits can depend on two different criteria. The first Voltage Limited Current ( $I_{voltage\ lim}$ , represented by the solid line), the second is Power Dissipation Limited Current ( $I_{power\ diss}$ ).

$$I_{voltage\ lim} = \frac{\sqrt{2}}{2} I_{peak} = \frac{\sqrt{2}}{2} \times \frac{V_{rated}}{X_C} = \sqrt{2} \pi F C V_{rated}$$

$I_{power\ diss} = \sqrt{\frac{P_{dissipation}}{ESR}}$  (If the thermal resistance of the mounting surface is 40°C/W, then you will reach the power dissipated limit of 1.5W)

## ≠ Capacitor Application Program

PPI's brand new online Capacitor Application Program (C.A.P.) helps Engineers and Designers select capacitors according to parameters such as cap value and frequency. C.A.P. allows engineers to insert capacitors requirements (Cap value, Frequency), producing Scattering Matrices (S2P) Charts while providing options (Case Size, Terminations, Mounting), and parameters (ESR, Q, Impedance) along with Datasheets. Once engineers have determined their capacitor requirements, C.A.P. also includes online Requests For Quotes (RFQs) and/or sample requests.



## ≠ Modelithics Vendor Program

PPI offers design engineers a Free 90-Day Trial license for the Modelithics PPI Component Library. This program provides engineers access to extremely accurate scalable simulation models for Passive Plus capacitors with advanced features that enable a more precise and rapid design process.

Microwave Global Models include every part value in a series and permit users to input substrate thickness, dielectric constant, and loss tangent, as well as mounting pad layout dimensions. Selected models also include capacitor orientation – vertical or horizontal – as an input. Engineers can request FREE use of the models by visiting the <https://www.modelithics.com/MVP/PPI>.



## ≠ Recommended Land Pattern Dimensions

Regarding Landing Patterns, please refer to IPC-7351B (table 3-5, 3-6).




Traditional High Q (>10,000) Low ESR  
Multi-Layer Ceramic Capacitors

**0505C/P (0.055" x 0.055")**

### ≠ Tape & Reel Specifications

Orientation	Measurement Unit	W	P0	P1	T	F	Minimum Qty per Reel	Std Qty per Reel	Tape Material
H	in.	0.315	0.157	0.157	0.009	0.138	500	3000	Plastic
	mm	8.00	4.00	4.00	0.22	3.50			
V	in.	0.472	0.157	0.157	0.012	0.217	500	2000	
	mm	12.00	4.00	4.00	0.30	5.50			

Note: Vertical Tape & Reel not available for all values. Contact PPI for availability.



A<sub>0</sub>B<sub>0</sub>K<sub>0</sub>

- Determined by component size. Typical clearance between the cavity and the component is: .50 (.002) min to .65 (.026) max for 12mm tape.
- The component cannot rotate more than 20° within the determined cavity.

### ≠ Engineering Design Kits

PPI offers Design Kits for engineers who are building and testing prototypes. Each kit contains 16 values; 10 pieces per value.



Kits are offered in Magnetic or Non-Magnetic Terminations. Kits are 100% RoHS compliant.

Kit Number		Value Range	Values	RoHS
MAGNETIC	NON-MAGNETIC			
DKD0505C01	DKD0505C05	0.1 - 2.0pF	0.1, 0.2, 0.3, 0.4, 0.5, 0.6, 0.7, 0.8, 0.9, 1.0, 1.2, 1.5, 1.6, 1.8, 2.0pF	✓
DKD0505P01	DKD0505P05			
DKD0505C02	DKD0505C06	1 - 10pF	1.0, 1.2, 1.5, 1.8, 2.0, 2.2, 2.4, 2.7, 3.0, 3.3, 3.9, 4.7, 5.6, 6.8, 8.2, 10pF	✓
DKD0505P02	DKD0505P06			
DKD0505C03	DKD0505C07	10 - 100pF	10, 12, 15, 18, 20, 22, 24, 27, 30, 33, 39, 47, 56, 68, 82, 100pF	✓
DKD0505P03	DKD0505P07			
DKD0505C04	DKD0505C08	100 - 1000pF	100, 120, 150, 180, 200, 220, 240, 270, 300, 330, 390, 470, 560, 680, 820, 1000pF	✓

**DKD0505C01**  
Passive Plus Inc.  
RF & Microwave Components  
**0505C Series 0.1 — 2.0pF**  
Size: 0.055" x 0.055"  
TC = NP0 WVDC = 150V  
Hi-Q Low ESR Capacitor Design Kit  
www.passiveplus.com

**DKD0505C02**  
Passive Plus Inc.  
RF & Microwave Components  
**0505C Series 1.0 — 10pF**  
Size: 0.055" x 0.055"  
TC = NP0 WVDC = 150V  
Hi-Q Low ESR Capacitor Design Kit  
www.passiveplus.com

**DKD0505C03**  
Passive Plus Inc.  
RF & Microwave Components  
**0505C Series 10 — 100pF**  
Size: 0.055" x 0.055"  
TC = NP0 WVDC = 150V  
Hi-Q Low ESR Capacitor Design Kit  
www.passiveplus.com

**DKD0505C04**  
Passive Plus Inc.  
RF & Microwave Components  
**0505C Series 100 — 1000pF**  
Size: 0.055" x 0.055"  
TC = NP0 WVDC = 150V  
Hi-Q Low ESR Capacitor Design Kit  
www.passiveplus.com

**DKD0505P01**  
Passive Plus Inc.  
RF & Microwave Components  
**0505P Series 0.1 — 2.0pF**  
Size: 0.055" x 0.055"  
TC = P90 WVDC = 150V  
Hi-Q Low ESR Capacitor Design Kit  
www.passiveplus.com

**DKD0505P02**  
Passive Plus Inc.  
RF & Microwave Components  
**0505P Series 1.0 — 10pF**  
Size: 0.055" x 0.055"  
TC = P90 WVDC = 150V  
Hi-Q Low ESR Capacitor Design Kit  
www.passiveplus.com

**DKD0505P03**  
Passive Plus Inc.  
RF & Microwave Components  
**0505P Series 10 — 100pF**  
Size: 0.055" x 0.055"  
TC = P90 WVDC = 150V  
Hi-Q Low ESR Capacitor Design Kit  
www.passiveplus.com



Traditional High Q (>10,000) Low ESR  
Multi-Layer Ceramic Capacitors

**1111C/P (0.110" x 0.110")**

### ≠ Product Features

- High Q
- High Power
- Low ESR/ESL
- Low Noise
- High Self-Resonance
- Ultra Stable Performance
- Capacitance Range:  
0.1pF to 1000pF
- Working Voltage: 500V
- Extended Voltage: 1500V

### ≠ Product Applications

#### Typical Functional Applications:

- Tuning • Bypass • Coupling
- Feedback • D.C. Blocking
- Impedance Matching


#### Typical Circuit Applications:

- UHF/Microwave RF Power Amplifiers
- Mixers • Oscillators • Filter Networks
- Low Noise Amplifiers • Timing Circuits  
and Delay Lines



Marking shown for illustration purposes only.  
Actual marking may differ.

### ≠ Part Numbering



### ≠ Capacitance Tolerance Codes

Code	A	B	C	D	F	G	J	K
<b>Tol.</b>	±0.05pF	±0.1pF	±0.25pF	±0.5pF	±1%	±2%	±5%	±10%

### ≠ Voltage Codes

Voltage	Code	Voltage	Code
50V	500	500V	501
100V	101	600V	601
200V	201	1000V	102
300V	301	1500V	152



Traditional High Q (>10,000) Low ESR  
Multi-Layer Ceramic Capacitors

**1111C/P (0.110" x 0.110")**

≠ 1111C/P Capacitance Values

- NP0=C; P90=P
- **Maximum Capacitance:** 1111P=1000pF; 1111C=10000pF
- \* - Available in NP0 only.

Special capacitances, tolerances and WVDC are available. Please contact PPI.



Marking shown for illustration purposes only.  
Actual marking may differ.

Cap. pF	Cap Code	Tol.	Rated WVDC		Cap. pF	Cap Code	Tol.	Rated WVDC		Cap. pF	Cap Code	Tol.	Rated WVDC		Cap. pF	Cap Code	Tol.	Rated WVDC	
			Std.	Ext.				Std.	Ext.				Std.	Ext.				Std.	Ext.
0.1	OR1	A,B	500V	1000V or 1500V	3.3	3R3	A,B C,D	500V	1000V or 1500V	36	360	F,G, J,K	500V	1000V or 1500V	390	391	F,G, J,K	200V	600V
0.2	OR2				3.6	3R6				39	390				430	431			
0.3	OR3				3.9	3R9				43	430				470	471			
0.4	OR4				4.3	4R3				47	470				510	511			
0.5	OR5	A,B, C,D	500V	1000V or 1500V	4.7	4R7	F,G, J,K	500V	1000V or 1500V	51	510	F,G, J,K	300V	1000V	560	561	F,G, J,K	100V	200V
0.6	OR6				5.1	5R1				56	560				620	621			
0.7	OR7				5.6	5R6				62	620				680	681			
0.8	OR8				6.2	6R2				68	680				750	751			
0.9	OR9				6.8	6R8				75	750				820	821			
1.0	1R0				7.5	7R5				82	820				910	911			
1.1	1R1				8.2	8R2				91	910				1000	102			
1.2	1R2				9.1	9R1				100	101				1100	112*			
1.3	1R3				10	100				110	111				1200	122*			
1.4	1R4				11	110				120	121				1500	152*			
1.5	1R5	12	120	130	131	1800	182*												
1.6	1R6	13	130	150	151	2000	202*												
1.7	1R7	15	150	160	161	2200	222*												
1.8	1R8	16	160	180	181	2700	272*												
1.9	1R9	18	180	200	201	3000	302*												
2.0	2R0	20	200	220	221	3300	332*												
2.1	2R1	22	220	240	241	4700	472*												
2.2	2R2	24	240	270	271	5100	512*												
2.4	2R4	27	270	300	301	5600	562*												
2.7	2R7	30	300	330	331	10000	103*												
3.0	3R0	33	330	360	361														

\*Available in NP0 only







Traditional High Q (>10,000) Low ESR  
Multi-Layer Ceramic Capacitors

**1111C/P (0.110" x 0.110")**

## ≠ Termination Types and Codes



Chip Termination:  
Codes: W, L, P



Microstrip Termination:  
Codes: MS, MN

### Magnetic Terminations

Termination Code	Termination
W	100% Tin Solder over Nickel Barrier
L	90%Tin/10%Lead Solder over Nickel Barrier

MS 100% Silver

### Non-Magnetic Termination

P 100% Tin  
Solder over Copper Barrier

MN Silver-Plated Copper

## ≠ Dimensions Unit: inch (millimeter)

Magnetic Termination								
Code		Capacitor Dimensions				Lead Dimensions		
		Length	Width	Thickness	Overlap	Length	Width	Thickness
		Lc	Wc	Tc	B	LL	WL	TL
W/L	Chip	0.110 (2.79)	$\begin{matrix} +0.025 \\ -0.010 \\ +0.36 \\ -0.25 \end{matrix}$ (2.79 ± 0.25)	0.110 ± 0.010 (2.54 max)	0.10 max (0.40 ~ 1.00)	-	-	-
MS	Microstrip	0.135 ± 0.015 (3.45 ± 0.38)	0.110 ± 0.010 (2.79 ± 0.25)	0.10 max (2.54 max)	-	0.250 min (6.35 min)	0.093 ± 0.010 (2.36 ± 0.25)	0.004 ± 0.001 (0.1 ± 0.025)

Non-Magnetic Termination								
Code		Capacitor Dimensions				Lead Dimensions		
		Length	Width	Thickness	Overlap	Length	Width	Thickness
		Lc	Wc	Tc	B	LL	WL	TL
P	Chip	0.110 (2.79)	$\begin{matrix} +0.025 \\ -0.010 \\ +0.36 \\ -0.25 \end{matrix}$ (2.79 ± 0.25)	0.110 ± 0.010 (2.54 max)	0.10 max (0.40 ~ 1.00)	-	-	-
MN	Microstrip	0.135 ± 0.015 (3.45 ± 0.38)	0.110 ± 0.010 (2.79 ± 0.25)	0.10 max (2.54 max)	-	0.250 min (6.35 min)	0.093 ± 0.010 (2.36 ± 0.25)	0.004 ± 0.001 (0.1 ± 0.025)

Note: Non-Magnetic means no magnetic materials. All leads are attached with high temperature solder and parts are RoHS Compliant.



Traditional High Q (>10,000) Low ESR  
Multi-Layer Ceramic Capacitors

**1111C/P (0.110" x 0.110")**

## ≠ Electrical Specifications

Quality Factor (Q)	Greater than 10,000 at 1 MHz
Insulation Resistance (IR)	0.1pF to 470pF:
	10 <sup>6</sup> Megaohms min. @ +25°C rated WVDC
	10 <sup>5</sup> Megaohms min. @ +125°C rated WVDC
	510pF to 1000pF:
	10 <sup>5</sup> Megaohms min. @ +25°C rated WVDC
	10 <sup>4</sup> Megaohms min. @ +125°C rated WVDC
Rated Voltage	See Rated Voltage in Capacitance Table
Dielectric Withstanding Voltage (DWV)	250% of Rated Voltage of 5 seconds, Rated Voltage ≤ 500VDC
	150% of Voltage for 5 seconds, 500VDC < Rated Voltage ≤ 1250 VDC
	120% of Voltage for 5 seconds, Rated Voltage > 1250 VDC
Operating Temperature Range	-55°C to 200°C
Temperature Coefficient (TC)	C: -55°C to 125°C 0±30ppm/°C;
	>125°C to 200°C 0±60ppm/°C
	P: -55°C to 200°C +90±20ppm/°C
Capacitance Drift	±0.02% or ±0.05pF, whichever is greater
Piezoelectric Effects	None
Termination Type	See Termination Type Table

Capacitors are designed and manufactured to meet the requirements of MIL-PRF-55681 and MIL-PRF-123.

## ≠ Environmental Specifications

	Specification	Test Parameters
Thermal Shock	<b>DWV:</b> The initial Value <b>IR:</b> Shall not be less than 30% of the initial value. <b>Capacitance Change:</b>	MIL-STD-202, Method 107, Condition A. At the maximum rated temperature (-55°C and 200°C) stay 30 minutes, the time of removing shall not be more than 3 minutes. Perform five cycles.
Moisture Resistance	No more than 0.5% or 0.5pF, whichever is greater.	MIL-STD-202, Method 106
Humidity (Steady State)	<b>DWV:</b> The initial Value <b>IR:</b> The initial value. <b>Capacitance Change:</b> No more than 0.3% or 0.3pF, whichever is greater.	MIL-STD-202, Method 103, Condition A With 1.5Volts DC applied while subjected to an environment of 85°C with 85% relative humidity for 240 hours minimum.
Life	<b>IR:</b> Shall not be less than 30% of the initial value. <b>Capacitance Change:</b> No more than 2.0% or 0.5pF, whichever is greater.	MIL-STD-202, Method 108. For 2000 hours, at 200°C. 200% of Voltage for Capacitors, Rated Voltage ≤ 500VDC; 120% of Voltage for Capacitors, 500VDC < Rated Voltage ≤ 1250VDC; 100% for Voltage for Capacitors, Rated Voltage > 1250VDC
Terminal Strength	<b>Force:</b> 10lbs typical, 5lbs. Minimum. <b>Duration Time:</b> 5 to 10 seconds	MIL-STD-202, Method 211A, Test Condition A. Applied a force and maintained for a period of 5 to 10 seconds. The force shall be in the direction of the axes of the terminations.



Traditional High Q (>10,000) Low ESR  
Multi-Layer Ceramic Capacitors


**1111C/P (0.110" x 0.110")**

## ≠ FPR -- First Parallel Resonance (FPRs)

### ≠ Definitions and Measurement Conditions

The **First Parallel Resonance, FPR**, is defined as the lowest frequency at which a suckout or notch appears in  $|S_{21}|$ .


It is generally independent of substrate thickness or dielectric constant, but does depend on capacitor orientation. A horizontal orientation means the capacitor electrode planes are parallel to the plane of the substrate; a vertical orientation means the electrode planes are perpendicular to the substrate.



## ≠ FSR -- First Series Resonance (FSRs)

### ≠ Definitions and Measurement Conditions

The **First Series Resonance, FSR**, is defined as the lowest frequency at which the imaginary part of the input impedance,  $\text{Im}[Z_{in}]$ , equals zero. Should  $\text{Im}[Z_{in}]$  or the real part of the input impedance,  $\text{Re}[Z_{in}]$ , not be monotonic with frequency at frequencies lower than those at which  $\text{Im}[Z_{in}] = 0$ , the FSR shall be considered as undefined (represented as a gap in the plot). FSR is dependent on internal capacitor structure; substrate thickness and dielectric constant; capacitor orientation, as defined alongside the FPR plot; and mounting pad dimensions.



The measurement conditions are: substrate – Rogers RO4350; substrate dielectric constant = 3.66; horizontal mount substrate thickness (mils) = 25; gap in microstrip trace (mils) = 15; horizontal mount microstrip trace width (mils) = 55. Reference planes at sample edges.

All data has been derived from electrical models created by Modelithics, Inc., a specialty vendor contracted by PPI. The models are derived from measurements on a large number of parts disposed on several different substrates.




Traditional High Q (>10,000) Low ESR  
Multi-Layer Ceramic Capacitors

**1111C/P (0.110" x 0.110")**

### ≠ ESR vs. Frequency

1111C/P ESR vs Frequency



1111C ESR vs Frequency





Traditional High Q (>10,000) Low ESR  
Multi-Layer Ceramic Capacitors


**1111C/P (0.110" x 0.110")**

**≠ Q vs. Capacitance**

1111C/P Q vs Frequency




1111C Q vs Frequency




**≠ Current Rating vs. Capacitance**

1111C/P Current Rating vs Capacitance



1111C Current Rating vs Capacitance




Current limits can depend on two different criteria. The first Voltage Limited Current ( $I_{voltage\ lim}$ , represented by the solid line), the second is Power Dissipation Limited Current ( $I_{power\ diss}$ ).

$$I_{voltage\ lim} = \frac{\sqrt{2}}{2} I_{peak} = \frac{\sqrt{2}}{2} \times \frac{V_{rated}}{X_C} = \sqrt{2} \pi F C V_{rated}$$

$I_{power\ diss} = \sqrt{\frac{P_{dissipation}}{ESR}}$  (If the thermal resistance of the mounting surface is 20°C/W, then you will reach the power dissipated limit of 3W)

## ≠ Capacitor Application Program

PPI's brand new online Capacitor Application Program (C.A.P.) helps Engineers and Designers select capacitors according to parameters such as cap value and frequency. C.A.P. allows engineers to insert capacitors requirements (Cap value, Frequency), producing Scattering Matrices (S2P) Charts while providing options (Case Size, Terminations, Mounting), and parameters (ESR, Q, Impedance) along with Datasheets. Once engineers have determined their capacitor requirements, C.A.P. also includes online Requests For Quotes (RFQs) and/or sample requests.



## ≠ Modelithics Vendor Program

PPI offers design engineers a Free 90-Day Trial license for the Modelithics PPI Component Library. This program provides engineers access to extremely accurate scalable simulation models for Passive Plus capacitors with advanced features that enable a more precise and rapid design process.

Microwave Global Models include every part value in a series and permit users to input substrate thickness, dielectric constant, and loss tangent, as well as mounting pad layout dimensions. Selected models also include capacitor orientation – vertical or horizontal – as an input. Engineers can request FREE use of the models by visiting the <https://www.modelithics.com/MVP/PPI>.



## ≠ Recommended Land Pattern Dimensions

Regarding Landing Patterns, please refer to IPC-7351B (table 3-5, 3-6).




Traditional High Q (>10,000) Low ESR  
Multi-Layer Ceramic Capacitors

**1111C/P (0.110" x 0.110")**

## ≠ Tape & Reel Specifications

Orientation	Measurement Unit	W	P0	P1	T	F	Minimum Qty per Reel	Std Qty per Reel	Tape Material
H	in.	0.315	0.157	0.157	0.009	0.138	500	2000	Plastic
	mm	8.00	4.00	4.00	0.22	3.50			
V	in.	0.315	0.157	0.157	0.009	0.138	500	1500	
	mm	8.00	4.00	4.00	0.22	3.50			
V	in.	0.472	0.157	0.157	0.016	0.217	500	1500	
	mm	12.00	4.00	4.00	0.40	5.50			



A<sub>0</sub>B<sub>0</sub>K<sub>0</sub>

- Determined by component size. Typical clearance between the cavity and the component is: .50 (.002) min to .65 (.026) max for 12mm tape.
- The component cannot rotate more than 20° within the determined cavity.

## ≠ Engineering Design Kits

PPI offers Design Kits for engineers who are building and testing prototypes. Each kit contains 16 values; 10 pieces per value.



Kits are offered in Magnetic or Non-Magnetic Terminations. Kits are 100% RoHS compliant.

Kit Number		Value Range	Values	RoHS
MAGNETIC	NON-MAGNETIC			
DKD1111C01	DKD1111C05	<b>1.0 - 10pF</b>	1.0, 1.2, 1.5, 1.8, 2.0, 2.2, 2.4, 2.7, 3.0, 3.3, 3.9, 4.7, 5.6, 6.8, 8.2, 10pF	✓
DKD1111P01	DKD1111P05			
DKD1111C02	DKD1111C06	<b>10 - 100pF</b>	10, 12, 15, 18, 20, 22, 24, 27, 30, 33, 39, 47, 56, 68, 82, 100pF	✓
DKD1111P02	DKD1111P06			
DKD1111C03	DKD1111C07	<b>100 - 1000pF</b>	100, 120, 150, 180, 200, 220, 240, 270, 300, 330, 390, 470, 560, 680, 820, 1000pF	✓
DKD1111P03	DKD1111P07			
DKD1111C04	DKD1111C08	<b>1000 - 10000pF</b>	1000, 1100, 1200, 1500, 1800, 2000, 2200, 2700, 3000, 3300, 3900, 4700, 5100, 5600, 10000pF	✓
DKD1111P04	DKD1111P08			

**DKD1111C01**  
1111C Series 1.0 — 10pF  
Size: 0.110" x 0.110"  
TC = NP0 WVDC = 500V  
Hi-Q Low ESR Capacitor Design Kit

**DKD1111C02**  
1111C Series 10 — 100pF  
Size: 0.110" x 0.110"  
TC = NP0 WVDC = 500V  
Hi-Q Low ESR Capacitor Design Kit

**DKD1111C03**  
1111C Series 100 — 1000pF  
Size: 0.110" x 0.110"  
TC = NP0 WVDC = 500V  
Hi-Q Low ESR Capacitor Design Kit

**DKD1111C04**  
1111C Series 1000 — 10000pF  
Size: 0.110" x 0.110"  
TC = NP0 WVDC = 100V  
Hi-Q Low ESR Capacitor Design Kit

**DKD1111P01**  
1111P Series 1.0 — 10pF  
Size: 0.110" x 0.110"  
TC = P90 WVDC = 500V  
Hi-Q Low ESR Capacitor Design Kit

**DKD1111P02**  
1111P Series 10 — 100pF  
Size: 0.110" x 0.110"  
TC = P90 WVDC = 500V  
Hi-Q Low ESR Capacitor Design Kit

**DKD1111P03**  
1111P Series 100 — 1000pF  
Size: 0.110" x 0.110"  
TC = P90 WVDC = 500V  
Hi-Q Low ESR Capacitor Design Kit

**DKD1111P04**  
1111P Series 1000 — 10000pF  
Size: 0.110" x 0.110"  
TC = P90 WVDC = 100V  
Hi-Q Low ESR Capacitor Design Kit



Traditional High Q (>10,000) Low ESR  
Multi-Layer Ceramic Capacitors

**2225C/P (0.220" x 0.250")**

### Product Features

- High Q
- High RF Current/Voltage
- Ultra Stable Performance
- Capacitance Range:  
0.5pF to 2700pF
- Working Voltage: 2500V
- Extended Voltage: 3600V

### Product Applications

#### Typical Functional Applications:

- Tuning • Bypass • Coupling
- Feedback • D.C. Blocking
- Impedance Matching


#### Typical Circuit Applications:

- UHF/Microwave RF Power Amplifiers
- Antenna Tuning • Plasma Chambers
- Medical Equipment



Marking shown for illustration purposes only.  
Actual marking may differ.

### Part Numbering



### Capacitance Tolerance Codes

Code	A	B	C	D	F	G	J	K
Tol.	±0.05pF	±0.1pF	±0.25pF	±0.5pF	±1%	±2%	±5%	±10%

### Voltage Codes

Voltage	Code	Voltage	Code
500V	501	2500V	252
1000V	102	3000V	302
1500V	152	3600V	362
2000V	202		






Traditional High Q (>10,000) Low ESR  
Multi-Layer Ceramic Capacitors

**2225C/P (0.220" x 0.250")**

≠ 2225C/P Capacitance Values


- NP0=C; P90=P

Special capacitances, tolerances and WVDC are available. Please contact PPI.




Cap. pF	Cap Code	Tol.	Rated WVDC		Cap. pF	Cap Code	Tol.	Rated WVDC		Cap. pF	Cap Code	Tol.	Rated WVDC		Cap. pF	Cap Code	Tol.	Rated WVDC	
			Std.	Ext.				Std.	Ext.				Std.	Ext.				Std.	Ext.
0.5	0R5				4.3	4R3				43	430				430	431	F,G, J,K	1500V	2000V
0.6	0R6				4.7	4R7				47	470				470	471			
0.7	0R7				5.1	5R1				51	510				510	511			
0.8	0R8				5.6	5R6				56	560				560	561			
0.9	0R9				6.2	6R2	B,C, D	2500V	3600V	62	620	F,G, J,K	2500V	3600V	620	621			
1.0	1R0				6.8	6R8				68	680				680	681			
1.1	1R1				7.5	7R5				75	750				750	751	F,G, J,K	1000V	1500V
1.2	1R2				8.2	8R2				82	820				820	821			
1.3	1R3				9.1	9R1				91	910				910	911			
1.4	1R4				10	100				100	101				1000	102			
1.5	1R5				11	110				110	111				1100	112			
1.6	1R6	B,C, D	2500V	3600V	12	120				120	121				1200	122			
1.7	1R7				13	130				130	131				1500	152			
1.8	1R8				15	150				150	151				1800	182	F,G, J,K	500V	N/A
1.9	1R9				16	160				160	161	F,G, J,K	2500V	3000V	2200	222			
2.0	2R0				18	180				180	181				2700	272			
2.1	2R1				20	200	F,G, J,K	2500V	3600V	200	201								
2.2	2R2				22	220				220	221								
2.4	2R4				24	240				240	241								
2.7	2R7				27	270				270	271								
3.0	3R0				30	300				300	301								
3.3	3R3				33	330				330	331	F,G, J,K	1500V	2000V					
3.6	3R6				36	360				360	361								
3.9	3R9				39	390				390	391								


### ≠ Termination Types and Codes




Chip Termination:  
Codes: W, L, P




Microstrip Termination:  
Codes: MS, MN




Axial Ribbon Termination:  
Code: AR, AN



Radial Wire Termination:  
Codes: RW, RN



Radial Ribbon Termination:  
Code: RR, FN



Axial Wire Termination:  
Codes: AW, BN

Termination Code	Magnetic Termination
W	100% Tin Solder over Nickel Barrier
L	90%Tin/10%Lead Solder over Nickel Barrier
MS	Silver-Plated Copper
AR	
RR	
RW	
AW	

Termination Code	Non-Magnetic
P	100% Tin Solder over Copper Barrier
MN	Silver-Plated Copper
AN	
FN	
RN	
BN	

Note: "Non-Magnetic" means no magnetic materials.



Traditional High Q (>10,000) Low ESR  
Multi-Layer Ceramic Capacitors

**2225C/P (0.220" x 0.250")**

≠ **Dimensions** - For Termination Types images, see previous page Unit: inch (millimeter)

Magnetic Termination								
Code		Capacitor Dimensions				Lead Dimensions		
		Length	Width	Thickness	Overlap	Length	Width	Thickness
		Lc	Wc	Tc	B	LL	WL	TL
W/L	Chip	0.225 (5.72)	$0.250 \pm 0.015$ (6.35 ± 0.38)	0.165 max (4.19 max)	0.020 ~ 0.047 (0.50 ~ 1.20)	-	-	-
MS	Microstrip					0.500 min (12.70 min)	0.240 ± 0.005 (6.1 ± 0.13)	0.008 ± 0.001 (0.2 ± 0.025)
AR	Axial Ribbon							
RR	Radial Ribbon	$0.245 \pm 0.025$ (6.22 ± 0.64)	$0.250 \pm 0.015$ (6.35 ± 0.38)	0.150 max (3.81 max)	-	0.354 min (9.00 min)	0.118 ± 0.005 (3.00 ± 0.13)	0.012 ± 0.001 (0.3 ± 0.025)
RW	Radio Wire					0.709 min (18.00 min)		Dia. = 0.031 ± 0.004
AW	Axial Wire					0.906 min (23.00 min)		Dia. = (0.80 ± 0.10)

Non-Magnetic Termination								
Code		Capacitor Dimensions				Lead Dimensions		
		Length	Width	Thickness	Overlap	Length	Width	Thickness
		Lc	Wc	Tc	B	LL	WL	TL
P	Chip	0.225 (5.72)	$0.250 \pm 0.015$ (6.35 ± 0.38)	0.165 max (4.19 max)	0.020 ~ 0.047 (0.50 ~ 1.20)	-	-	-
MN	Microstrip					0.500 min (12.70 min)	0.240 ± 0.005 (6.1 ± 0.13)	0.008 ± 0.001 (0.2 ± 0.025)
AN	Axial Ribbon							
FN	Radial Ribbon	$0.245 \pm 0.025$ (6.22 ± 0.64)	$0.250 \pm 0.015$ (6.35 ± 0.38)	0.150 max (3.81 max)	-	0.354 min (9.00 min)	0.118 ± 0.005 (3.00 ± 0.13)	0.012 ± 0.001 (0.3 ± 0.025)
RN	Radio Wire					0.709 min (18.00 min)		Dia. = 0.031 ± 0.004
BN	Axial Wire					0.906 min (23.00 min)		Dia. = (0.80 ± 0.10)

⊗ Note: Non-Magnetic means no magnetic materials. All leads are attached with high temperature solder and parts are RoHS Compliant.



Traditional High Q (>10,000) Low ESR  
Multi-Layer Ceramic Capacitors

**2225C/P (0.220" x 0.250")**

## ⚡ Electrical Specifications

Quality Factor (Q)	Greater than 10,000 at 1 MHz
Insulation Resistance (IR)	Test Voltage: 500V 10 <sup>5</sup> Megaohms min. @ +25°C 10 <sup>4</sup> Megaohms min. @ +125°C
Rated Voltage	See Rated Voltage in Capacitance Table
Dielectric Withstanding Voltage (DWV)	250% of Rated Voltage of 5 seconds, Rated Voltage ≤ 500VDC 150% of Voltage for 5 seconds, 500VDC < Rated Voltage ≤ 1250 VDC 120% of Voltage for 5 seconds, Rated Voltage > 1250 VDC
Operating Temperature Range	-55°C to 200°C
Temperature Coefficient (TC)	C: -55°C to 125°C 0±30ppm/°C; >125°C to 200°C 0±60ppm/°C P: -55°C to 200°C +90±20ppm/°C
Capacitance Drift	±0.02% or ±0.02pF, whichever is greater
Piezoelectric Effects	None
Termination Type	See Termination Type Table

Capacitors are designed and manufactured to meet the requirements of MIL-PRF-55681 and MIL-PRF-123.

## ⚡ Environmental Specifications

	Specification	Test Parameters
Thermal Shock	<b>DWV:</b> The initial Value <b>IR:</b> Shall not be less than 30% of the initial value. <b>Capacitance Change:</b>	MIL-STD-202, Method 107, Condition A. At the maximum rated temperature (-55°C and 200°C) stay 30 minutes, the time of removing shall not be more than 3 minutes. Perform five cycles.
Moisture Resistance	No more than 0.5% or 0.5pF, whichever is greater.	MIL-STD-202, Method 106
Humidity (Steady State)	<b>DWV:</b> The initial Value <b>IR:</b> The initial value. <b>Capacitance Change:</b> No more than 0.3% or 0.3pF, whichever is greater.	MIL-STD-202, Method 103, Condition A With 1.5Volts DC applied while subjected to an environment of 85°C with 85% relative humidity for 240 hours minimum.
Life	<b>IR:</b> Shall not be less than 30% of the initial value. <b>Capacitance Change:</b> No more than 2.0% or 0.5pF, whichever is greater.	MIL-STD-202, Method 108. For 2000 hours, at 200°C. 200% of Voltage for Capacitors, Rated Voltage ≤ 500VDC; 120% of Voltage for Capacitors, 500VDC < Rated Voltage ≤ 1250VDC; 100% for Voltage for Capacitors, Rated Voltage > 1250VDC
Terminal Strength	<b>Force:</b> 20lbs typical, 10lbs. Minimum. <b>Duration Time:</b> 5 to 10 seconds	MIL-STD-202, Method 211A, Test Condition A. Applied a force and maintained for a period of 5 to 10 seconds. The force shall be in the direction of the axes of the terminations.




Traditional High Q (>10,000) Low ESR  
Multi-Layer Ceramic Capacitors

**2225C/P (0.220" x 0.250")**


### ≠ Series Resonance vs. Capacitance

Series Resonance vs. Capacitance



### ≠ ESR vs. Frequency

2225C/P ESR vs Frequency






Traditional High Q (>10,000) Low ESR  
Multi-Layer Ceramic Capacitors

**2225C/P (0.220" x 0.250")**


### ≠ Q vs. Capacitance

Q vs Capacitance




### ≠ Current Rating vs. Capacitance

2225C/P Current Rating vs Capacitance



## ≠ Current Rating vs. Capacitance

2225C/P Current Rating vs Capacitance



Current limits can depend on two different criteria. The first Voltage Limited Current ( $I_{\text{voltage lim}}$ , represented by the solid line), the second is Power Dissipation Limited Current ( $I_{\text{power diss}}$ ).

$$I_{\text{voltage lim}} = \frac{\sqrt{2}}{2} I_{\text{peak}} = \frac{\sqrt{2}}{2} \times \frac{V_{\text{rated}}}{X_C} = \sqrt{2} \pi F C V_{\text{rated}}$$

$I_{\text{power diss}} = \sqrt{\frac{P_{\text{dissipation}}}{\text{ESR}}}$  (If the thermal resistance of the mounting surface is 15°C/W, then you will reach the power dissipated limit of 4W)




Traditional High Q (>10,000) Low ESR  
Multi-Layer Ceramic Capacitors

**2225C/P (0.220" x 0.250")**

## ≠ Capacitor Application Program

PPI's brand new online Capacitor Application Program (C.A.P.) helps Engineers and Designers select capacitors according to parameters such as cap value and frequency. C.A.P. allows engineers to insert capacitors requirements (Cap value, Frequency), producing Scattering Matrices (S2P) Charts while providing options (Case Size, Terminations, Mounting), and parameters (ESR, Q, Impedance) along with Datasheets. Once engineers have determined their capacitor requirements, C.A.P. also includes online Requests For Quotes (RFQs) and/or sample requests.




## ≠ Recommended Land Pattern Dimensions

Regarding Landing Patterns, please refer to IPC-7351B (table 3-5, 3-6).

## ≠ Custom Assemblies

Passive Plus offers Capacitor Assemblies for high power requirements. Typical assemblies are configured in series and/or parallel combinations, producing higher voltage/current handling capabilities, extended capacitance range and tighter tolerances.

To get started, simply send us either a mechanical drawing or circuit conditions and we can recommend a solution. All components are 100% up-screened for Partial Discharge and Sonoscanned. All assemblies include a 100hr Military burn in.








Traditional High Q (>10,000) Low ESR  
Multi-Layer Ceramic Capacitors

**2225C/P (0.220" x 0.250")**

**≠ Tape & Reel Specifications (mm)**

Orientation	Measurement Unit	W	P0	P1	T	F	Minimum Qty per Reel	Std Qty per Reel	Tape Material
H	in.	0.630	0.157	0.472	0.012	0.295	500	500	Plastic
	mm	16.00	4.00	12.00	0.30	7.50			
V	in.	0.630	0.157	0.315	0.020	0.295	500	500	Plastic
	mm	16.00	4.00	8.00	0.50	7.50			



A<sub>0</sub>B<sub>0</sub>K<sub>0</sub>

- Determined by component size. Typical clearance between the cavity and the component is: .50 (.002) min to .65 (.026) max for 12mm tape.
- The component cannot rotate more than 20° within the determined cavity.



Traditional High Q (>10,000) Low ESR  
Multi-Layer Ceramic Capacitors

**3838C/P (0.380" x 0.380")**

**≠ Product Features**

- High Q
- High RF Current/Voltage
- Ultra Stable Performance
- Capacitance Range:  
0.5pF to 5100pF
- Working Voltage: 3600V
- Extended Voltage: 7200V


**≠ Product Applications**

**Typical Functional Applications:**

- Tuning • Bypass • Coupling
- D.C. Blocking • Impedance Matching


**Typical Circuit Applications:**

- HF/RF Power Amplifiers
- Antenna Tuning • Plasma Chambers
- Medical Equipment • Transmitters



Marking shown for illustration purposes only.  
Actual marking may differ.

**≠ Part Numbering**



**≠ Capacitance Tolerance Codes**

Code	A	B	C	D	F	G	J	K
Tol.	±0.05pF	±0.1pF	±0.25pF	±0.5pF	±1%	±2%	±5%	±10%

**≠ Voltage Codes**

Voltage	Code
500V	501
1000V	102
2500V	252
3600V	362
7200V	722




Traditional High Q (>10,000) Low ESR  
Multi-Layer Ceramic Capacitors

**3838C/P (0.380" x 0.380")**


≠ 3838C/P Capacitance Values

Special capacitances, tolerances and WVDC are available. Please contact PPI.




Cap. pF	Cap Code	Tol.	Rated WVDC		Cap. pF	Cap Code	Tol.	Rated WVDC		Cap. pF	Cap Code	Tol.	Rated WVDC		Cap. pF	Cap Code	Tol.	Rated WVDC
			Std.	Ext.				Std.	Ext.				Std.	Ext.				
0.5	OR5	B,C, D	3600V	7200V	4.7	4R7	B,C, D	3600V	7200V	51	510	F,G, J,K	3600V	7200V	560	561	F,G, J,K	2500V
0.6	OR6				5.1	5R1				56	560				620	621		
0.7	OR7				5.6	5R6				62	620				680	681		
0.8	OR8				6.2	6R2				68	680				750	751		
0.9	OR9				6.8	6R8				75	750				820	821		
1.0	1R0				7.5	7R5				82	820				910	911		
1.1	1R1				8.2	8R2				91	910				1000	102		
1.2	1R2				9.1	9R1				100	101				1100	112		
1.3	1R3				10	100				110	111				1200	122		
1.4	1R4				11	110	120	121	1500	152								
1.5	1R5				12	120	130	131	1800	182								
1.6	1R6				13	130	150	151	2200	222								
1.7	1R7				15	150	160	161	2400	242								
1.8	1R8				16	160	180	181	2700	272								
1.9	1R9				18	180	200	201	3000	302								
2.0	2R0				20	200	220	221	3300	332								
2.1	2R1				22	220	240	241	3600	362								
2.2	2R2				24	240	270	271	3900	392								
2.4	2R4				27	270	300	301	4300	432								
2.7	2R7	30	300	330	331	4700	472											
3.0	3R0	33	330	360	361	5100	512											
3.3	3R3	36	360	390	391													
3.6	3R6	39	390	430	431													
3.9	3R9	43	430	470	471	F,G, J,K	2500V	N/A										
4.3	4R3	47	470	510	511													


### ≠ Termination Types and Codes




Chip Termination:  
Codes: W, L, P




Microstrip Termination:  
Codes: MS, MN




Axial Ribbon Termination:  
Code: AR, AN



Radial Wire Termination:  
Codes: RW, RN



Radial Ribbon Termination:  
Code: RR, FN



Axial Wire Termination:  
Codes: AW, BN

Termination Code	Magnetic Termination
W	100% Tin Solder over Nickel Barrier
L	90%Tin/10%Lead Solder over Nickel Barrier
MS	Silver-Plated Copper
AR	
RR	
RW	
AW	

Termination Code	Non-Magnetic
P	100% Tin Solder over Copper Barrier
MN	Silver-Plated Copper
AN	
FN	
RN	
BN	

Note: "Non-Magnetic" means no magnetic materials.



Traditional High Q (>10,000) Low ESR  
Multi-Layer Ceramic Capacitors

**3838C/P (0.380" x 0.380")**

≠ **Dimensions** - For Termination Types images, see previous page Unit: inch (millimeter)

Magnetic Termination									
Code		Capacitor Dimensions				Lead Dimensions			
		Length	Width	Thickness	Overlap	Length	Width	Thickness	
		Lc	Wc	Tc	B	LL	WL	TL	
W/L	Chip	0.380 (9.65	$\begin{matrix} +0.015 \\ -0.010 \\ +0.38 \\ -0.25 \end{matrix}$ )	$0.380 \pm 0.010$ (9.65 ± 0.25)	0.170 max (4.32 max)	0.024 ~ 0.059 (0.60 ~ 1.50)	-	-	-
MS	Microstrip					0.728 min (18.50 min)	$0.350 \pm 0.020$ (8.89 ± 0.50)	$0.008 \pm 0.001$ (0.20 ± 0.025)	
AR	Axial Ribbon					0.728 min (18.50 min)	$0.315 \pm 0.010$ (8.00 ± 0.25)	$0.008 \pm 0.001$ (0.20 ± 0.025)	
RR	Radial Ribbon	0.380 (9.65	$\begin{matrix} +0.015 \\ -0.010 \\ +0.38 \\ -0.25 \end{matrix}$ )	$0.380 \pm 0.010$ (9.65 ± 0.25)	0.177 max (4.50 max)	-	0.354 min (9.00 min)	$0.118 \pm 0.005$ (3.00 ± 0.13)	$0.012 \pm 0.001$ (0.3 ± 0.025)
RW	Radio Wire					0.709 min (18.00 min)		Dia. = $0.031 \pm 0.004$	
AW	Axial Wire					0.906 min (23.00 min)		Dia. = $(0.80 \pm 0.10)$	

Non-Magnetic Termination									
Code		Capacitor Dimensions				Lead Dimensions			
		Length	Width	Thickness	Overlap	Length	Width	Thickness	
		Lc	Wc	Tc	B	LL	WL	TL	
P	Chip	0.380 (9.65	$\begin{matrix} +0.015 \\ -0.010 \\ +0.38 \\ -0.25 \end{matrix}$ )	$0.380 \pm 0.010$ (9.65 ± 0.25)	0.170 max (4.32 max)	0.024 ~ 0.059 (0.60 ~ 1.50)	-	-	-
MN	Microstrip					0.728 min (18.50 min)	$0.350 \pm 0.020$ (8.89 ± 0.50)	$0.008 \pm 0.001$ (0.20 ± 0.025)	
AN	Axial Ribbon					0.728 min (18.50 min)	$0.315 \pm 0.010$ (8.00 ± 0.25)	$0.008 \pm 0.001$ (0.20 ± 0.025)	
FN	Radial Ribbon	0.380 (9.65	$\begin{matrix} +0.015 \\ -0.010 \\ +0.38 \\ -0.25 \end{matrix}$ )	$0.380 \pm 0.010$ (9.65 ± 0.25)	0.177 max (4.50 max)	-	0.354 min (9.00 min)	$0.118 \pm 0.005$ (3.00 ± 0.13)	$0.012 \pm 0.001$ (0.3 ± 0.025)
RN	Radio Wire					0.709 min (18.00 min)		Dia. = $0.031 \pm 0.004$	
BN	Axial Wire					0.906 min (23.00 min)		Dia. = $(0.80 \pm 0.10)$	

⊗ Note: Non-Magnetic means no magnetic materials. All leads are attached with high temperature solder and parts are RoHS Compliant.



Traditional High Q (>10,000) Low ESR  
Multi-Layer Ceramic Capacitors

**3838C/P (0.380" x 0.380")**

## ⚡ Electrical Specifications

Quality Factor (Q)	Greater than 10,000 at 1 MHz
Insulation Resistance (IR)	Test Voltage: 500V 10 <sup>5</sup> Megaohms min. @ +25°C 10 <sup>4</sup> Megaohms min. @ +125°C
Rated Voltage	See Rated Voltage in Capacitance Table
Dielectric Withstanding Voltage (DWV)	250% of Rated Voltage of 5 seconds, Rated Voltage ≤ 500VDC 150% of Voltage for 5 seconds, 500VDC < Rated Voltage ≤ 1250 VDC 120% of Voltage for 5 seconds, Rated Voltage > 1250 VDC
Operating Temperature Range	-55°C to 200°C
Temperature Coefficient (TC)	C: -55°C to 125°C 0±30ppm/°C; >125°C to 200°C 0±60ppm/°C P: -55°C to 200°C +90±20ppm/°C
Capacitance Drift	±0.02% or ±0.02pF, whichever is greater
Piezoelectric Effects	None
Termination Type	See Termination Type Table

## ⚡ Environmental Specifications

	Specification	Test Parameters
Thermal Shock	<b>DWV:</b> The initial value <b>IR:</b> Shall not be less than 30% of the initial value. <b>Capacitance Change:</b>	MIL-STD-202, Method 107, Condition A. At the maximum rated temperature (-55°C and 200°C) stay 30 minutes, the time of removing shall not be more than 3 minutes. Perform five cycles.
Moisture Resistance	No more than 0.5% or 0.5pF, whichever is greater.	MIL-STD-202, Method 106
Humidity (Steady State)	<b>DWV:</b> The initial value <b>IR:</b> The initial value <b>Capacitance Change:</b> No more than 0.3% or 0.3pF, whichever is greater.	MIL-STD-202, Method 103, Condition A With 1.5Volts DC applied while subjected to an environment of 85°C with 85% relative humidity for 240 hours minimum.
Life	<b>IR:</b> Shall not be less than 30% of the initial value. <b>Capacitance Change:</b> No more than 2.0% or 0.5pF, whichever is greater.	MIL-STD-202, Method 108. For 2000 hours, at 200°C. 200% of Voltage for Capacitors, Rated Voltage ≤ 500VDC; 120% of Voltage for Capacitors, 500VDC < Rated Voltage ≤ 1250VDC; 100% for Voltage for Capacitors, Rated Voltage > 1250VDC
Terminal Strength	<b>Force:</b> 20lbs typical, 10lbs. min. <b>Duration Time:</b> 5 to 10 seconds	MIL-STD-202, Method 211A, Test Condition A. Applied a force and maintained for a period of 5 to 10 seconds. The force shall be in the direction of the axes of the terminations.


Capacitors are designed and manufactured to meet the requirements of MIL-PRF-55681 and MIL-PRF-123.




Traditional High Q (>10,000) Low ESR  
Multi-Layer Ceramic Capacitors

**3838C/P (0.380" x 0.380")**

### ≠ Series Resonance vs. Capacitance



### ≠ ESR vs. Frequency







Traditional High Q (>10,000) Low ESR  
Multi-Layer Ceramic Capacitors

**3838C/P (0.380" x 0.380")**

**≠ Q vs. Capacitance**



**≠ Current Rating vs. Capacitance**



Current limits can depend on two different criteria. The first Voltage Limited Current ( $I_{voltage\ lim}$ , represented by the solid line), the second is Power Dissipation Limited Current ( $I_{pow\ diss}$ ).

$$I_{voltage\ lim} = \frac{\sqrt{2}}{2} I_{peak} = \frac{\sqrt{2}}{2} \times \frac{V_{rated}}{X_C} = \sqrt{2}\pi F C V_{rated}$$

$I_{pow\ diss} = \sqrt{\frac{P_{dissipation}}{ESR}}$  (If the thermal resistance of the mounting surface is 12°C/W, then you will reach the power dissipated limit of 5W)





Traditional High Q (>10,000) Low ESR  
Multi-Layer Ceramic Capacitors

**3838C/P (0.380" x 0.380")**


### ≠ Recommended Land Pattern Dimensions

Regarding Landing Patterns, please refer to IPC-7351B (table 3-5, 3-6).

### ≠ Custom Assemblies


Passive Plus offers Capacitor Assemblies for high power requirements. Typical assemblies are configured in series and/or parallel combinations, producing higher voltage/current handling capabilities, extended capacitance range and tighter tolerances.

To get started, simply send us either a mechanical drawing or circuit conditions and we can recommend a solution. All components are 100% up-screened for Partial Discharge and Sonoscanned. All assemblies include a 100hr Military burn in.



### ≠ Tape & Reel Specifications (mm)

Orientation	Measurement Unit	W	P0	P1	T	F	Minimum Qty per Reel	Std Qty per Reel	Tape Material
H	in.	0.630	0.157	0.630	0.012	0.295	50	200	Plastic
	mm	16.00	4.00	16.00	0.30	7.50			



A<sub>0</sub>B<sub>0</sub>K<sub>0</sub>

- Determined by component size. Typical clearance between the cavity and the component is: .50 (.002) min to .65 (.026) max for 12mm tape.
- The component cannot rotate more than 20° within the determined cavity.




### ≠ Product Features

- High Q
- High RF Current/Voltage
- Ultra Stable Performance
- Capacitance Range:  
1.0pF to 6800pF
- Working Voltage: 5000V
- Extended Voltage: 8000V


### ≠ Typical Circuit Applications

- Semiconductor Manufacturing
- High Energy Power Transfers
- Plasma Chambers
- Medical Equipment



Marking shown for illustration purposes only.  
Actual marking may differ.

### ≠ Part Numbering



### ≠ Capacitance Tolerance Codes

Code	B	C	D	F	G	J	K
Tol.	±0.1pF	±0.25pF	±0.5pF	±1%	±2%	±5%	±10%

### ≠ Voltage Codes

Voltage	Code
1000V	102
2000V	202
3000V	302
5000V	502
8000V	802



UHF/RF High-Q Power Transmitter  
Multi-Layer Ceramic Capacitors

**6040C (0.600" x 0.400")**

**± 6040C Capacitance Values**


For special capacitances, tolerances and WVDC, please contact PPI.




Marking shown for illustration purposes only.  
Actual marking may differ.

Cap. pF	Cap Code	Tol.	Rated WVDC		Cap. pF	Cap Code	Tol.	Rated WVDC		Cap. pF	Cap Code	Tol.	Rated WVDC	
			Std.	Ext.				Std.	Ext.				Std.	Ext.
1.0	1R0	B,C, D	5000V	8000V	39	390	F,G, J,K	5000V	8000V	1500	152	F,G, J,K	2000V	3000V
1.2	1R2				47	470				1800	182			
1.5	1R5				56	560				2200	222			
1.8	1R8				68	680				2700	272			
2.2	2R2				82	820				3300	332			
2.7	2R7				100	101				4700	472			
3.3	3R3				120	121				5100	512			
3.9	3R9				150	151				5600	562			
4.7	4R7				180	181				6800	682			
5.6	5R6				220	221								
6.8	6R8	F,G, J,K	5000V	8000V	270	271	F,G, J,K	3000V	5000V					
8.2	8R2				330	331								
10	100				390	391								
12	120				470	471								
15	150				560	561								
18	180				680	681								
22	220				820	821				F,G, J,K	2000V	3000V		
27	270				1000	102								
33	330				1200	122								


## ≠ Termination Types and Codes




Chip Termination:  
Codes: **W, L, P**




Microstrip Termination:  
Codes: **MS, MN**















Axial Ribbon Termination:  
Code: **AR, AN**



Radial Wire Termination:  
Codes: **RW, RN**



Axial Wire Termination:  
Codes: **AW, BN**

Termination Code	Magnetic Termination	Termination Code	Non-Magnetic  Termination
<b>W</b> 	100% Tin Solder over Nickel Barrier	<b>P</b> 	100% Tin Solder over Copper Barrier
<b>L</b>	90%Tin/10%Lead Solder over Nickel Barrier	<b>MN</b> 	Silver-Plated Copper
<b>MS</b> 		<b>AN</b> 	
<b>AR</b> 		<b>RN</b> 	
<b>RW</b> 	Silver-Plated Copper	<b>BN</b> 	
<b>AW</b> 		 Note: "Non-Magnetic" means no magnetic materials.	



≠ **Dimensions** - For Termination Types images, see previous page Unit: inch (millimeter)

Magnetic Termination								
Code		Capacitor Dimensions				Lead Dimensions		
		Length	Width	Thickness	Overlap	Length	Width	Thickness
		Lc	Wc	Tc	B	LL	WL	TL
W/L	Chip	0.614 (15.6)	$\begin{matrix} +0.015 \\ -0.010 \\ +0.38 \\ -0.25 \end{matrix}$	$0.433 \pm 0.010$ (11.0 ± 0.25)	$0.154 \pm 0.008$ (3.90 ± 0.20)	0.063 max (1.60 max)	-	-
MS	Microstrip					0.787 min (20.0 min)	$0.350 \pm 0.010$ (8.89 ± 0.50)	$0.008 \pm 0.001$ (0.20 ± 0.025)
AR	Axial Ribbon	0.614	$\begin{matrix} +0.015 \\ -0.010 \end{matrix}$	$0.433 \pm 0.010$	$0.154 \pm 0.008$	0.787 min (20.0 min)	$0.350 \pm 0.010$ (8.89 ± 0.50)	$0.008 \pm 0.001$ (0.20 ± 0.025)
RW	Radio Wire	(15.6)	$\begin{matrix} +0.38 \\ -0.25 \end{matrix}$	$(11.0 \pm 0.25)$	$(3.90 \pm 0.20)$	0.787 min (20.0 min)	Dia. = $0.030 \pm 0.004$	
AW	Axial Wire					0.984 min (25.00 min)	Dia. = $(0.80 \pm 0.10)$	

Non-Magnetic Termination								
Code		Capacitor Dimensions				Lead Dimensions		
		Length	Width	Thickness	Overlap	Length	Width	Thickness
		Lc	Wc	Tc	B	LL	WL	TL
P	Chip	0.614 (15.6)	$\begin{matrix} +0.015 \\ -0.010 \\ +0.38 \\ -0.25 \end{matrix}$	$0.433 \pm 0.010$ (11.0 ± 0.25)	$0.154 \pm 0.008$ (3.90 ± 0.20)	0.063 max (1.60 max)	-	-
MN	Microstrip					0.787 min (20.0 min)	$0.350 \pm 0.010$ (8.89 ± 0.50)	$0.008 \pm 0.001$ (0.20 ± 0.025)
AN	Axial Ribbon	0.614	$\begin{matrix} +0.015 \\ -0.010 \end{matrix}$	$0.433 \pm 0.010$	$0.154 \pm 0.008$	0.787 min (20.0 min)	$0.350 \pm 0.010$ (8.89 ± 0.50)	$0.008 \pm 0.001$ (0.20 ± 0.025)
RN	Radio Wire	(15.6)	$\begin{matrix} +0.38 \\ -0.25 \end{matrix}$	$(11.0 \pm 0.25)$	$(3.90 \pm 0.20)$	0.787 min (20.0 min)	Dia. = $0.030 \pm 0.004$	
BN	Axial Wire					0.984 min (25.00 min)	Dia. = $(0.80 \pm 0.10)$	

⊘ Note: Non-Magnetic means no magnetic materials. All leads are attached with high temperature solder and parts are RoHS Compliant.



## ≠ Electrical Specifications

Quality Factor (Q)	No less than 1000pF, Q value more than 2000, Test Frequency 1MHz; More than 1000pF, Q value more than 2000, Test Frequency 1MHz
Insulation Resistance (IR)	Test Voltage: 500V 10 <sup>5</sup> Megaohms min. @ +25°C 10 <sup>4</sup> Megaohms min. @ +125°C
Rated Voltage	See Rated Voltage in Capacitance Table
Dielectric Withstanding Voltage (DWV)	250% of Voltage of 5 seconds, Rated Voltage ≤ 500VDC 150% of Voltage for 5 seconds, 500VDC < Rated Voltage ≤ 1250 VDC 120% of Voltage for 5 seconds, Rated Voltage > 1250 VDC
Operating Temperature Range	-55°C to 175°C
Temperature Coefficient (TC)	-55°C to 125°C 0±30ppm/°C >125°C to 175°C 0±60ppm/°C
Capacitance Drift	±0.02% or ±0.02pF, whichever is greater
Piezoelectric Effects	None
Termination Type	See Termination Type Table

## ≠ Environmental Specifications

	Specification	Test Parameters
Thermal Shock	<b>DWV:</b> The initial value <b>IR:</b> Shall not be less than 30% of the initial value. <b>Capacitance Change:</b>	MIL-STD-202, Method 107, Condition A. At the maximum rated temperature (-55°C and 175°C) stay 30 minutes, the time of removing shall not be more than 3 minutes. Perform five cycles.
Moisture Resistance	No more than 0.5% or 0.5pF, whichever is greater.	MIL-STD-202, Method 106
Humidity (Steady State)	<b>DWV:</b> The initial value <b>IR:</b> The initial value <b>Capacitance Change:</b> No more than 0.3% or 0.3pF, whichever is greater.	MIL-STD-202, Method 103, Condition A With 1.5Volts DC applied while subjected to an environment of 85°C with 85% relative humidity for 240 hours minimum.
Life	<b>IR:</b> Shall not be less than 30% of the initial value. <b>Capacitance Change:</b> No more than 2.0% or 0.5pF, whichever is greater.	MIL-STD-202, Method 108. For 2000 hours, at 125°C. 200% of Voltage for Capacitors, Rated Voltage ≤ 500VDC; 120% of Voltage for Capacitors, 500VDC < Rated Voltage ≤ 1250VDC; 100% for Voltage for Capacitors, Rated Voltage > 1250VDC
Terminal Strength	<b>Force:</b> 25lbs typical, 20lbs. min. <b>Duration Time:</b> 5 to 10 seconds	MIL-STD-202, Method 211A, Test Condition A. Applied a force and maintained for a period of 5 to 10 seconds. The force shall be in the direction of the axes of the terminations.


Capacitors are designed and manufactured to meet the requirements of MIL-PRF-55681 and MIL-PRF-123.




UHF/RF High-Q Power Transmitter  
Multi-Layer Ceramic Capacitors

**6040C (0.600" x 0.400")**

**≠ ESR vs. Capacitance Measured @ 30MHz**




**≠ Self Resonant Frequency vs. Capacitance**






**≠ Strip Terminals Rated Current vs. Frequency**




**≠ Wire Terminals Rated Current vs. Frequency**





### ≠ % Maximum Current vs. Ambient Temperature




### ≠ Recommended Land Pattern Dimensions

Regarding Landing Patterns, please refer to IPC-7351B (table 3-5, 3-6).

### ≠ Custom Assemblies

Passive Plus offers Capacitor Assemblies for high power requirements. Typical assemblies are configured in series and/or parallel combinations, producing higher voltage/current handling capabilities, extended capacitance range and tighter tolerances.

To get started, simply send us either a mechanical drawing or circuit conditions and we can recommend a solution. All components are 100% up-screened for Partial Discharge and Sonoscanned. All assemblies include a 100hr Military burn in.





≠ **Product Features**

- High Q
- High RF Current/Voltage
- Ultra Stable Performance
- Capacitance Range:  
1.0pF to 20000pF
- Working Voltage: 5000V
- Extended Voltage: 8000V


≠ **Typical Circuit Applications**

- Semiconductor Manufacturing
- High Energy Power Transfers
- Plasma Chambers
- Medical Equipment



Marking shown for illustration purposes only.  
Actual marking may differ.

≠ **Part Numbering**



≠ **Capacitance Tolerance Codes**

Code	B	C	D	F	G	J	K
Tol.	±0.1pF	±0.25pF	±0.5pF	±1%	±2%	±5%	±10%

≠ **Voltage Codes**

Voltage	Code
1000V	102
2000V	202
3000V	302
5000V	502
8000V	802



**≠ 7676C Capacitance Values**


Special capacitances, tolerances and WVDC are available. Please contact PPI.




Marking shown for illustration purposes only.  
Actual marking may differ.

Cap. pF	Cap Code	Tol.	Rated WVDC		Cap. pF	Cap Code	Tol.	Rated WVDC		Cap. pF	Cap Code	Tol.	Rated WVDC	
			Std.	Ext.				Std.	Ext.				Std.	Ext.
1.0	1R0	B,C, D	5000V	8000V	33	330	F,G, J,K	5000V	8000V	1000	102	G,J, K	3000V	5000V
1.2	1R2				39	390				1200	122			
1.5	1R5				47	470				1500	152			
1.8	1R8				56	560				1800	182			
2.2	2R2				68	680				2200	222			
2.7	2R7				82	820				2700	272			
3.3	3R3				100	101				3300	332			
3.9	3R9				120	121				4700	472			
4.7	4R7				150	151				5100	512			
5.6	5R6				180	181				5600	562			
6.8	6R8	220	221	6800	682	G,J, K	1000V	3000V						
8.2	8R2	270	271	7500	752									
10	100	300	301	8200	822									
12	120	F,G, J,K	5000V	8000V	390	391	F,G, J,K	3000V	5000V	10000	103	G,J, K	1000V	2000V
15	150				470	471				12000	123			
18	180				560	561				15000	153			
22	220				680	681				18000	183			
27	270				820	821				20000	203			


**≠ Termination Types and Codes**




Chip Termination:  
Codes: **W, L, P**




Microstrip Termination:  
Codes: **MS, MN**









Axial Ribbon Termination:  
Code: **AR, AN**









Radial Wire Termination:  
Codes: **RW, RN**



Axial Wire Termination:  
Codes: **AW, BN**

Termination Code	Magnetic Termination
W 	100% Tin Solder over Nickel Barrier
L 	90%Tin/10%Lead Solder over Nickel Barrier
MS 	
AR 	
RW 	Silver-Plated Copper
AW 	

Termination Code	Non-Magnetic  Termination
P 	100% Tin Solder over Copper Barrier
MN 	
AN 	
RN 	Silver-Plated Copper
BN 	

 Note: "Non-Magnetic" means no magnetic materials.



**≠ Dimensions** - For Termination Types images, see previous page Unit: inch (millimeter)

		Magnetic Termination					Lead Dimensions		
Code		Capacitor Dimensions			Overlap	Length	Width	Thickness	
		Length	Width	Thickness					
		Lc	Wc	Tc	B	LL	WL	TL	
W/L	Chip	0.760 (19.3)	$0.760 \pm 0.010$ (19.3 ± 0.25)	0.197 max (5.00 max)	0.024 ~ 0.059 (0.60 ~ 1.50)	-	-	-	
MS	Microstrip					0.748 min (19.0 min)	$0.591 \pm 0.010$ (15.00 ± 0.25)	$0.008 \pm 0.001$ (0.20 ± 0.025)	
AR	Axial Ribbon	0.760 (19.3)	$0.760 \pm 0.010$ (19.3 ± 0.25)	0.197 max (5.00 max)	-	0.748 min (19.0 min)	$0.591 \pm 0.010$ (15.00 ± 0.25)	$0.008 \pm 0.001$ (0.20 ± 0.025)	
RW	Radio Wire					0.748 min (19.0 min)			
AW	Axial Wire					0.906 min (23.00 min)			
							Dia. = $0.031 \pm 0.006$ Dia. = (0.80 ± 0.15)		

		Non-Magnetic Termination					Lead Dimensions		
Code		Capacitor Dimensions			Overlap	Length	Width	Thickness	
		Length	Width	Thickness					
		Lc	Wc	Tc	B	LL	WL	TL	
P	Chip	0.760 (19.3)	$0.760 \pm 0.010$ (19.3 ± 0.25)	0.197 max (5.00 max)	0.024 ~ 0.059 (0.60 ~ 1.50)	-	-	-	
MN	Microstrip					0.748 min (19.0 min)	$0.591 \pm 0.010$ (15.00 ± 0.25)	$0.008 \pm 0.001$ (0.20 ± 0.025)	
AN	Axial Ribbon	0.760 (19.3)	$0.760 \pm 0.010$ (19.3 ± 0.25)	0.197 max (5.00 max)	-	0.748 min (19.0 min)	$0.591 \pm 0.010$ (15.00 ± 0.25)	$0.008 \pm 0.001$ (0.20 ± 0.025)	
RN	Radio Wire					0.748 min (19.0 min)			
BN	Axial Wire					0.906 min (23.00 min)			
							Dia. = $0.031 \pm 0.006$ Dia. = (0.80 ± 0.15)		

⊗ Note: Non-Magnetic means no magnetic materials. All leads are attached with high temperature solder and parts are RoHS Compliant.



## ⚡ Electrical Specifications


Quality Factor (Q)	No less than 1000pF, Q value more than 2000, Test Frequency 1MHz; More than 1000pF, Q value more than 2000, Test Frequency 1kHz
Insulation Resistance (IR)	Test Voltage: 500V 10 <sup>5</sup> Megaohms min. @ +25°C 10 <sup>4</sup> Megaohms min. @ +125°C
Rated Voltage	See Rated Voltage in Capacitance Table
Dielectric Withstanding Voltage (DWV)	250% of Voltage of 5 seconds, Rated Voltage ≤ 500VDC 150% of Voltage for 5 seconds, 500VDC < Rated Voltage ≤ 1250 VDC 120% of Voltage for 5 seconds, Rated Voltage > 1250 VDC
Operating Temperature Range	-55°C to 175°C
Temperature Coefficient (TC)	-55°C to 125°C 0±30ppm/°C >125°C to 175°C 0±60ppm/°C
Capacitance Drift	±0.2% or ±0.05pF, whichever is greater
Piezoelectric Effects	None
Termination Type	See Termination Type Table

## ⚡ Environmental Specifications


	Specification	Test Parameters
Thermal Shock	<b>DWV:</b> The initial value <b>IR:</b> Shall not be less than 30% of the initial value. <b>Capacitance Change:</b>	MIL-STD-202, Method 107, Condition A. At the maximum rated temperature (-55°C and 175°C) stay 30 minutes, the time of removing shall not be more than 3 minutes. Perform five cycles.
Moisture Resistance	No more than 0.5% or 0.5pF, whichever is greater.	MIL-STD-202, Method 106
Humidity (Steady State)	<b>DWV:</b> The initial value <b>IR:</b> The initial value <b>Capacitance Change:</b> No more than 0.3% or 0.3pF, whichever is greater.	MIL-STD-202, Method 103, Condition A With 1.5Volts DC applied while subjected to an environment of 85°C with 85% relative humidity for 240 hours minimum.
Life	<b>IR:</b> Shall not be less than 30% of the initial value. <b>Capacitance Change:</b> No more than 2.0% or 0.5pF, whichever is greater.	MIL-STD-202, Method 108. For 2000 hours, at 125°C. 200% of Voltage for Capacitors, Rated Voltage ≤ 500VDC; 120% of Voltage for Capacitors, 500VDC < Rated Voltage ≤ 1250VDC; 100% for Voltage for Capacitors, Rated Voltage > 1250VDC
Terminal Strength	<b>Force:</b> 30lbs. min. <b>Duration Time:</b> 5 to 10 seconds	MIL-STD-202, Method 211A, Test Condition A. Applied a force and maintained for a period of 5 to 10 seconds. The force shall be in the direction of the axes of the terminations.

Capacitors are designed and manufactured to meet the requirements of MIL-PRF-55681 and MIL-PRF-123.


≠ ESR vs. Capacitance Measured @ 30MHz




≠ Self Resonant Frequency vs. Capacitance



≠ Strip Terminals Rated Current vs. Frequency




≠ Wire Terminals Rated Current vs. Frequency





## ≠ % Maximum Current vs. Ambient Temperature




## ≠ Recommended Land Pattern Dimensions

Regarding Landing Patterns, please refer to IPC-7351B (Table 3-5, 3-6).

## ≠ Custom Assemblies

Passive Plus offers Capacitor Assemblies for high power requirements. Typical assemblies are configured in series and/or parallel combinations, producing higher voltage/current handling capabilities, extended capacitance range and tighter tolerances.

To get started, simply send us either a mechanical drawing or circuit conditions and we can recommend a solution. All components are 100% up-screened for Partial Discharge and Sonoscanned. All assemblies include a 100hr Military burn in.





### ≠ Product Features

- High Q
- High RF Current/Voltage
- Ultra Stable Performance
- Capacitance Range:  
200pF to 120000pF
- Working Voltage: 10000V


### ≠ Typical Circuit Applications

- Semiconductor Manufacturing
- High Energy Power Transfers
- Plasma Chambers
- Medical Equipment



Marking shown for illustration purposes only.  
Actual marking may differ.

### ≠ Part Numbering



### ≠ Capacitance Tolerance Codes

Code	G	J	K
Tol.	±2%	±5%	±10%

### ≠ Voltage Codes

Voltage	Code
1000V	102
3000V	302
5000V	502
10000V	103



UHF/RF High-Q Power Transmitter  
Multi-Layer Ceramic Capacitors

**1313C (1.30" x 1.30")**

≠ 1313C Capacitance Values


For special capacitances, tolerances and WVDC, please contact PPI.




Marking shown for illustration purposes only.  
Actual marking may differ.

Cap. pF	Cap Code	Tol.	Rated WVDC	Cap. pF	Cap Code	Tol.	Rated WVDC	Cap. pF	Cap Code	Tol.	Rated WVDC
200	201	G,J, K	10kV	1800	182	G,J, K	10kV	12000	123	J,K	3000V
220	221			2200	222			15000	153		
270	271			2700	272			22000	223		
300	301			3300	332	33000	333				
330	331			4700	472	47000	473				
390	391			5100	512	56000	563				
470	471			5600	562	68000	683	J,K	1000V		
560	561			6800	682	82000	823				
680	681			7500	752	100000	104				
820	821			10000	103	120000	124				
1000	102										
1200	122										
1500	152										


**≠ Termination Types and Codes**




Chip Termination:  
Codes: **L, P**



Microstrip Termination:  
Codes: **MN**



Axial Ribbon Termination:  
Code: **AN**



Radial Wire Termination:  
Codes: **FN**

Termination Code	Magnetic Termination
<b>L</b>	90% Sn10%Pb Tin/Lead Solder over Nickel Plating

Termination Code	Non-Magnetic Terminations
<b>P</b>	100% Sn Solder over Copper Plating
<b>MN</b>	
<b>AN</b>	Silver-Plated Copper
<b>FN</b>	

Note: "Non-Magnetic" means no magnetic materials.



≠ **Dimensions** - For Termination Types images, see previous page Unit: inch (millimeter)

Magnetic Termination								
Code		Capacitor Dimensions			Lead Dimensions			
		Length	Width	Thickness	Overlap	Length	Width	Thickness
		Lc	Wc	Tc	B	LL	WL	TL
L	Chip	1.350 ± 0.050	1.350 ± 0.050	0.197 max	0.039 ~ 0.071	-	-	-
		(34.29 ± 1.27)	(34.29 ± 1.27)	(5.00 max)	(1.00 ~ 1.80)			

Non-Magnetic Termination								
Code		Capacitor Dimensions			Lead Dimensions			
		Length	Width	Thickness	Overlap	Length	Width	Thickness
		Lc	Wc	Tc	B	LL	WL	TL
P	Chip	1.350 ± 0.050	1.350 ± 0.050	0.197 max	0.039 ~ 0.071	-	-	-
		(34.29 ± 1.27)	(34.29 ± 1.27)	(5.00 max)	(1.00 ~ 1.80)			
MN	Microstrip	1.350 ± 0.050	1.350 ± 0.050	0.197 max	-	0.748 min	1.299 ± 0.020	0.012 ± 0.001
		(34.29 ± 1.27)	(34.29 ± 1.27)	(5.00 max)		(19.0 min)	(33.00 ± 0.50)	(0.30 ± 0.025)
AN	Axial Ribbon	1.350 ± 0.050	1.350 ± 0.050	0.197 max	-	0.748 min	1.299 ± 0.020	0.012 ± 0.001
		(34.29 ± 1.27)	(34.29 ± 1.27)	(5.00 max)		(19.0 min)	(33.00 ± 0.50)	(0.30 ± 0.025)
FN	Radial Ribbon	1.350 ± 0.050	1.350 ± 0.050	0.197 max	-	0.699 min	0.157 ± 0.010	0.008 ± 0.001
		(34.29 ± 1.27)	(34.29 ± 1.27)	(5.00 max)		(17.0 min)	(4.00 ± 0.25)	(0.20 ± 0.025)

⊗ Note: Non-Magnetic means no magnetic materials. All leads are attached with high temperature solder and parts are RoHS Compliant.



## ≠ Electrical Specifications


Quality Factor (Q)	No less than 1000pF, Q value more than 2000, Test Frequency 1MHz; More than 1000pF, Q value more than 2000, Test Frequency 1kHz
Insulation Resistance (IR)	Test Voltage: 500V 10 <sup>5</sup> Megaohms min. @ +25°C rated WVDC 10 <sup>4</sup> Megaohms min. @ +125°C rated WVDC
Rated Voltage	See Rated Voltage Table
Dielectric Withstanding Voltage (WVDC)	250% of Voltage of 5 seconds, Rated Voltage ≤ 500VDC 150% of Voltage for 5 seconds, 500VDC < Rated Voltage ≤ 1250 VDC 120% of Voltage for 5 seconds, Rated Voltage > 1250 VDC
Operating Temperature Range	-55°C to 175°C
Temperature Coefficient (TC)	-55°C to 125°C 0±30ppm/°C >125°C to 175°C 0±60ppm/°C
Capacitance Drift	±0.02% or ±0.02pF, whichever is greater
Piezoelectric Effects	None
Termination Type	See Termination Type Table

Capacitors are designed and manufactured to meet the requirements of MIL-PRF-55681 and MIL-PRF-123.


## ≠ Environmental Specifications

	Specification	Test Parameters
Thermal Shock	<b>DWV:</b> The initial value <b>IR:</b> Shall not be less than 30% of the initial value. <b>Capacitance Change:</b>	MIL-STD-202, Method 107, Condition A. At the maximum rated temperature (-55°C and 175°C) stay 30 minutes, the time of removing shall not be more than 3 minutes. Perform five cycles.
Moisture Resistance	No more than 0.5% or 0.5pF, whichever is greater.	MIL-STD-202, Method 106
Humidity (Steady State)	<b>DWV:</b> The initial value <b>IR:</b> The initial value <b>Capacitance Change:</b> No more than 0.3% or 0.3pF, whichever is greater.	MIL-STD-202, Method 103, Condition A With 1.5Volts DC applied while subjected to an environment of 85°C with 85% relative humidity for 240 hours minimum.
Life	<b>IR:</b> Shall not be less than 30% of the initial value. <b>Capacitance Change:</b> No more than 2.0% or 0.5pF, whichever is greater.	MIL-STD-202, Method 108. For 2000 hours, at 125°C. 200% of Voltage for Capacitors, Rated Voltage ≤ 500VDC; 120% of Voltage for Capacitors, 500VDC < Rated Voltage ≤ 1250VDC; 100% for Voltage for Capacitors, Rated Voltage > 1250VDC
Terminal Strength	<b>Force:</b> 30lbs. min. <b>Duration Time:</b> 5 to 10 seconds	MIL-STD-202, Method 211A, Test Condition A. Applied a force and maintained for a period of 5 to 10 seconds. The force shall be in the direction of the axes of the terminations.


≠ ESR vs. Capacitance Measured @ 30MHz



≠ Self Resonant Frequency vs. Capacitance



### ⚡ Rated Current vs. Frequency




### ⚡ Recommended Land Pattern Dimensions

Regarding Landing Patterns, please refer to IPC-7351B (table 3-5, 3-6).

### ⚡ Custom Assemblies

Passive Plus offers Capacitor Assemblies for high power requirements. Typical assemblies are configured in series and/or parallel combinations, producing higher voltage/current handling capabilities, extended capacitance range and tighter tolerances.

To get started, simply send us either a mechanical drawing or circuit conditions and we can recommend a solution. All components are 100% up-screened for Partial Discharge and Sonoscanned. All assemblies include a 100hr Military burn in.











UHF/RF High-Q Power Transmitter  
Multi-Layer Ceramic Capacitors

## Custom Capacitor Assemblies



*Marking shown for illustration purposes only.  
Actual marking may differ.*

Please contact PPI ([sales@passiveplus.com](mailto:sales@passiveplus.com)) to discuss custom assembly options.



**≠ Product Features**

High Operating Voltage, High Operating Current, Extended Capacitance,  
Tighter Tolerances, High Reliability, High Q, Ultra-low ESR, Non-Magnetic


**≠ Typical Applications Field**

High Power RF, Medical Electronics, Broadcast, Semiconductor Manufacturing,  
High Magnetic Environments, Inductive Heating

**≠ Part Numbering**



*Marking shown for illustration purposes only.  
Actual marking may differ.*



Capacitor Size:

11 = 1111; 22 = 2225; 38 = 3838; 60 = 6040; 76 = 7676

Capacitance: For capacitor values requiring 3 significant digits,

e.g. 1222.5pF =1222R5

e.g. P6S22P101F252X

Silver bracket assembly with six 2225C pieces in parallel, Capacitance is 100pF,

Capacitance tolerance is ±1%, WVDC is 2500 V and Laser marking.

e.g. S2S25C1222R5G203X

Silver bracket assembly with two 2225C pieces in series, Capacitance is 1222.5pF,

Capacitance tolerance is ±2%, WVDC is 20,000V and Laser marking.

**≠ Capacitance and Voltage**

By Buyer's requirements using existing drawings, mechanical sketches, or we can help with capable modeling of assemblies thermal rise predictions.




≠ Typical Assembly Configurations

≠ Parallel Assemblies

unit:inch (millimeter)

	1111C/P	22225C/P	3838C/P	6040C	7676C
Lead Material	Silver plated Copper or Silver				
Lead Thickness	.004 or .010 (0.1 or 0.25)			.010 or .020 (0.25 or 0.51)	
Lead Length (max.)	.50 (12.7)	.75 (19.8)		2.0 (50.8)	
Capacitor Spacer (typ.)	.050 or .078 (1.3 or 2)			.090 (2.3)	.050 or .157 (1.3 or 4)
Mounting Configuration	Horizontal / Vertical				



3838 Series/Parallel Combination




Marking shown for illustration purposes only. Actual marking may differ.

≠ Series Assemblies

unit:inch (millimeter)

	22225C/P	3838C/P	6040C	7676C
Lead Type	L Bracket			
Lead Material	Silver plated Copper or Silver			
Lead Thickness	.010 ( 0.25)		.010 or .020 (0.25 or 0.51)	
Lead Length (max.)	.75 (19.8)	1.0 (25.4)		
Capacitor Spacer (typ.)	.050 or .157 (1.3 or 4)			
Mounting Configuration	Horizontal			

- Epoxy Molding Available



Marking shown for illustration purposes only. Actual marking may differ.

Other Assemblies: By Buyer's requirement. Contact PPI.



# EIA Low ESR Microwave Capacitors


## Product Features

- Lowest ESR
- Low Noise
- High Self-Resonance

## Product Applications

### Typical Functional Applications



- Tuning • Bypass • Coupling
- Feedback • D.C. Blocking
- Impedance Matching



### Typical Circuit Applications

- UHF/Microwave RF Power Amplifiers
- Mixers • Oscillators • Filter Networks
- Low Noise Amplifiers • Timing Circuits and Delay Lines

## Part Numbering



## Case Size (Chip) Dimensions

	0201	0402	0603	0708	0805	1111
<b>Length</b> <b>Lc</b>	0.024 ± 0.001 (0.60 ± 0.03)	0.040 ± 0.004 (1.02 ± 0.10)	0.062 ± 0.006 (1.57 ± 0.15)	0.065 ± 0.006 (1.65 ± 0.15)	0.080 ± 0.008 (2.03 ± 0.20)	0.110 ± 0.015 (2.79 ± 0.38)
<b>Width</b> <b>Wc</b>	0.012 ± 0.001 (0.30 ± 0.03)	0.020 ± 0.004 (0.51 ± 0.10)	0.032 ± 0.006 (0.81 ± 0.15)	0.080 ± 0.006 (2.02 ± 0.15)	0.050 ± 0.008 (1.27 ± 0.20)	0.110 ± 0.015 (2.79 ± 0.38)
<b>Thickness</b> <b>Tc</b>	0.012 ± 0.001 (0.30 ± 0.03)	0.020 ± 0.004 (0.51 ± 0.10)	0.030 ± 0.003 (0.76 ± 0.08)	0.100 ± 0.008 (2.54 ± 0.20)	0.040 ± 0.006 (1.02 ± 0.15)	0.10 max (2.60 max)
<b>Overlap</b> <b>B</b>	0.008 (0.20)	0.010 ± 0.006 (0.25 ± 0.15)	0.014 ± 0.006 (0.35 ± 0.15)	0.020 ± 0.004 (0.50 ± 0.10)	0.020 ± 0.010 (0.50 ± 0.25)	0.015 max (0.025 max)



# EIA Low ESR Microwave Capacitors

## ≠ Temperature Coefficient

N:  $0 \pm 30 \text{ppm}/^\circ\text{C}$

## ≠ Rated Capacitance


Capacitance is less than 10pF; for example: 1R0=1.0pF, R denotes decimal point

Capacitance greater than 10pF; for example: 101=100pF, the third number is the power of 10

## ≠ Tolerance

Capacitance Tolerance								
Code	A	B	C	D	F	G	J	K
Tolerance	$\pm 0.05\text{pF}$	$\pm 0.1\text{pF}$	$\pm 0.25\text{pF}$	$\pm 0.5\text{pF}$	$\pm 1\%$	$\pm 2\%$	$\pm 5\%$	$\pm 10\%$

## ≠ Termination Types and Codes

Termination Code	Type	Magnetic Termination
W 	Chip	100% Sn Solder over Nickel Plating
L	Chip	90% Sn10%Pb Tin/Lead Solder over Nickel Plating

## ≠ Voltages

Code	Rated Voltage
250	25V
500	50V
251	250V
501	500V
102	1000V



## EIA Low ESR Microwave Capacitors

### ≠ Laser Marking

An “X” at the end of the part number indicates the part is marked.

Laser Marking is available on the 0805N & 1111N case sizes.

### ≠ Packing Orientation Option

TV: Tape carrier packaging Vertical Orientation.

Vertical orientation means that if the part is lifted from the tape without any rotation and placed on a substrate, its electrodes will be perpendicular to the substrate plane. This extends the frequency of the First Parallel Resonance (FPR), typically twice the FPR of an equivalent part mounted horizontally.

### ≠ Performance Requirements

Capacitors are designed and manufactured to meet the requirements of MIL-PRF-55681 and MIL-PRF-123.

All products are in compliance with RoHS instruction.





**≠ Product Features**

- High Q
- High Power
- Low ESR/ESL
- Low Noise
- High Self-Resonance
- Ultra Stable Performance
- Capacitance Range:  
0.1pF to 47pF
- Working Voltage: 50V


**≠ Product Applications**

**Typical Functional Applications:**


- Tuning • Bypass • Coupling
- Feedback • D.C. Blocking
- Impedance Matching

**Typical Circuit Applications:**

- UHF/Microwave RF Power Amplifiers
- Mixers • Oscillators • Filter Networks
- Low Noise Amplifiers • Timing Circuits and Delay Lines




**≠ Part Numbering**



**≠ Capacitor Dimensions**

Unit: inch (millimeter)

Code	Term.	Length	Width	Thickness	Overlap
		Lc	Wc	Tc	B
W	Chip	0.024 ± 0.001 (0.60 ± 0.03)	0.012 ± 0.001 (0.30 ± 0.03)	0.012 ± 0.001 (0.30 ± 0.03)	0.008 (0.20)



**≠ Capacitance Tolerance Codes**

Code	A	B	C	D	F	G	J	K
Tol.	±0.05pF	±0.1pF	±0.25pF	±0.5pF	±1%	±2%	±5%	±10%



≠ Terminations Type and Code

≠ Voltage Codes

Termination Code	Termination
W	100% Tin Solder over Nickel Barrier

Voltage	Code
25V	250
50V	500



≠ 0201N Capacitance Values

For special capacitances, tolerances and WVDC, please contact PPI.

Cap. pF	Cap Code	Tol.	Rated WVDC		Cap. pF	Cap Code	Tol.	Rated WVDC		Cap. pF	Cap Code	Tol.	Rated WVD		
			Std.	Ext.				Std.	Ext.				Std.	Ext.	
0.1	0R1	A*,B, C,	25V	50V	2.2	2R2	A*,B, C,	25V	50V	16	160	F,G, J,K	25V	50V	
0.2	0R2				2.4	2R4				18	180				
0.3	0R3				2.7	2R7				20	200				
0.4	0R4				3.0	3R0				22	220				
0.5	0R5				3.3	3R3				24	240				
0.6	0R6				3.6	3R6				27	270				
0.7	0R7				3.9	3R9				30	300				
0.8	0R8				4.3	4R3				33	330				
0.9	0R9				4.7	4R7				36	360				
1.0	1R0				5.1	5R1				39	390				
1.1	1R1	B,C, D	25V	50V	5.6	5R6	B,C, D	25V	50V	43	430				
1.2	1R2				6.2	6R2				47	470				
1.3	1R3				6.8	6R8									
1.4	1R4				7.5	7R5									
1.5	1R5				8.2	8R2									
1.6	1R6				9.1	9R1									
1.7	1R7				10	100									
1.8	1R8				11	110									
1.9	1R9				12	120				F,G, J,K	25V				50V
2.0	2R0				13	130									
2.1	2R1	15	150												

\*For A-tolerance parts, contact factory for availability





## ≠ Electrical Specifications

Quality Factor (Q)	2,000 at 1 MHz min.
Insulation Resistance (IR)	10 <sup>5</sup> Megaohms min. @ +25°C rated WVDC 10 <sup>4</sup> Megaohms min. @ +125°C rated WVDC
Rated Voltage	25V or 50V
Dielectric Withstanding Voltage (WVDC)	250% of Rated Voltage of 5 seconds
Operating Temperature Range	-55°C to 175°C
Temperature Coefficient (TC)	0±30ppm/°C
Capacitance Drift	±0.02% or ±0.02pF, whichever is greater
Piezoelectric Effects	None



## ≠ Environmental Specifications

	Specification	Test Parameters
Thermal Shock	No mechanical damage <b>Capacitance Change:</b> ±0.5% or 0.5pF max <b>IR:</b> >10 G Ohms Q>2000 Breakdown Voltage: 2.5x WVDC	MIL-STD-202, Method 107, Condition A. At the maximum rated temperature (-55°C and 175°C) stay 30 minutes, the time of removing shall not be more than 3 minutes. Perform five cycles.
Humidity (Steady State)	No mechanical damage <b>Capacitance Change:</b> ±0.5% or 0.5pF max <b>IR:</b> >1 G Ohms Q>300 Breakdown Voltage: 2.5x WVDC	MIL-STD-202, Method 106
Low Voltage Humidity	No mechanical damage <b>Capacitance Change:</b> ±0.3% or 0.3pF max <b>IR:</b> >1 G Ohms Q>300 Breakdown Voltage: 2.5x WVDC	MIL-STD-202, Method 103, Condition A, with 1.5 Volts DC applied while subjected to an environment of 85°C with 85% relative humidity for 240 hours minimum.
Life	No mechanical damage <b>Capacitance Change:</b> ±2.0% or 0.5pF max <b>IR:</b> >1 G Ohms Q>500 Breakdown Voltage: 2.5x WVDC	MIL-STD-202, Method 108. For 1000 hours, at 175°C. 200% of Voltage for Capacitors
Terminal Adhesion	Termination should not pull off. Ceramic should remain undamaged	Linear pull force exerted on axial leads soldered to each terminal 2.0lbs.
Resistance to Soldering Heat	No mechanical damage <b>Capacitance Change:</b> -1.0%~+2.0% <b>IR:</b> >10 G Ohms Q>500 Breakdown Voltage: 2.5x WVDC	Preheat device to 150°C -180°C for 60 seconds. Dip in 260°C ±5°C solder for 10 ±1 second. Measure after 24± 2 hour cooling period.


Capacitors are designed and manufactured to meet the requirements of MIL-PRF-55681 and MIL-PRF-123.



≠ ESR vs. Frequency



## ≠ First Parallel Resonance




## ≠ Definitions and Measurement Conditions

The **First Parallel Resonance**, **FPR**, is defined as the lowest frequency at which a suckout or notch appears in  $|S_{21}|$ . It is generally independent of substrate thickness or dielectric constant, but does depend on capacitor orientation. A vertical orientation means the electrode planes are perpendicular to the substrate.

The definitions on the charts are for a capacitor in a series configuration, i.e., mounted across a gap in a microstrip trace with 50-Ohm termination. The measurement conditions are: substrate – Rogers RO3006; substrate dielectric constant = 6.15; substrate thickness (mils) = 10; gap in microstrip trace (mils) = 6.0; microstrip trace width (mils) = 14.1; Reference planes at sample edges.

All data has been derived from electrical models created by Modelithics, Inc., a specialty vendor contracted by PPI. The models are derived from measurements on a large number of parts disposed on several different substrates.

## ≠ First Series Resonance



## ≠ Definitions and Measurement Conditions


The **First Series Resonance, FSR**, is defined as the lowest frequency at which the imaginary part of the input impedance,  $\text{Im}[Z_{in}]$ , equals zero. Should  $\text{Im}[Z_{in}]$  or the real part of the input impedance,  $\text{Re}[Z_{in}]$ , not be monotonic with frequency at frequencies lower than those at which  $\text{Im}[Z_{in}] = 0$ , the FSR shall be considered as undefined (represented as a gap in the plot). FSR is dependent on internal capacitor structure; substrate thickness and dielectric constant; capacitor orientation, as defined alongside the FPR plot; and mounting pad dimensions.

The definitions on the charts are for a capacitor in a series configuration, i.e., mounted across a gap in a microstrip trace with 50-Ohm termination. The measurement conditions are: substrate – Rogers RO3006; substrate dielectric constant = 6.15; substrate thickness (mils) = 10; gap in microstrip trace (mils) = 6.0; microstrip trace width (mils) = 14.1; Reference planes at sample edges.

All data has been derived from electrical models created by Modelithics, Inc., a specialty vendor contracted by PPI. The models are derived from measurements on a large number of parts disposed on several different substrates.

## ≠ Capacitor Application Program

PPI's brand new online Capacitor Application Program (C.A.P.) helps Engineers and Designers select capacitors according to parameters such as cap value and frequency. C.A.P. allows engineers to insert capacitors requirements (Cap value, Frequency), producing Scattering Matrices (S2P) Charts while providing options (Case Size, Terminations, Mounting), and parameters (ESR, Q, Impedance) along with Datasheets. Once engineers have determined their capacitor requirements, C.A.P. also includes online Requests For Quotes (RFQs) and/or sample requests.



## ≠ Modelithics Vendor Program

PPI offers design engineers a Free 90-Day Trial license for the Modelithics PPI Component Library. This program provides engineers access to extremely accurate scalable simulation models for Passive Plus capacitors with advanced features that enable a more precise and rapid design process.

Microwave Global Models include every part value in a series and permit users to input substrate thickness, dielectric constant, and loss tangent, as well as mounting pad layout dimensions. Selected models also include capacitor orientation – vertical or horizontal – as an input. Engineers can request FREE use of the models by visiting the <https://www.modelithics.com/MVP/PPI>.



## ≠ Recommended Land Pattern Dimensions


Regarding Landing Patterns, please refer to IPC-7351B (table 3-5, 3-6).



### ≠ Tape & Reel Specifications

Dimensions: mm

Orientation	Measurement Unit	W	P0	P1	T	F	Minimum Qty per Reel	Std Qty per Reel	Tape Material
H	in. mm	0.315 8.00	0.157 4.00	0.079 2.00	0.017 0.42	0.138 3.50	1000	15000	Paper



A<sub>0</sub>B<sub>0</sub>K<sub>0</sub>

- Determined by component size. Typical clearance between the cavity and the component is: .50 (.002) min to .65 (.026) max for 12mm tape.
- The component cannot rotate more than 20° within the determined cavity.

### ≠ Engineering Design Kits

PPI offers Design Kits for engineers who are building and testing prototypes. Each kit contains 10 pieces per value.

Kits are 100% RoHS compliant.



Kit Number	Value Range	Values	
DKD0201N01	<b>0.1 - 2.0pF</b>	0.1, 0.2, 0.3, 0.5, 0.7, 0.8, 0.9, 1.0, 1.3, 1.5, 1.7, 1.9, 2.0pF	
DKD0201N02	<b>1.0 - 10pF</b>	1.0, 1.3, 1.5, 1.7, 1.9, 2.0, 2.2, 2.7, 3.0, 3.9, 4.7, 5.6, 6.8, 7.5, 8.2, 10pF	
DKD0201N03	<b>10 - 47pF</b>	10, 13, 15, 18, 20, 22, 27, 30, 39, 47pF	

**DKD0201N01**

**0201N Series 0.1 — 2.0pF**

Size: 0.020" x 0.010"  
TC = NP0 WVDC = 50V

**Hi-Q Low ESR Capacitor Design Kit**

[www.passiveplus.com](http://www.passiveplus.com)

**DKD0201N02**

**0201N Series 1.0 — 10pF**

Size: 0.020" x 0.010"  
TC = NP0 WVDC = 50V

**Hi-Q Low ESR Capacitor Design Kit**

[www.passiveplus.com](http://www.passiveplus.com)

**DKD0201N03**

**0201N Series 10 — 47pF**

Size: 0.020" x 0.010"  
TC = NP0 WVDC = 50V

**Hi-Q Low ESR Capacitor Design Kit**

[www.passiveplus.com](http://www.passiveplus.com)



### ≠ Product Features

- High Q
- High Power
- Low ESR/ESL
- Low Noise
- High Self-Resonance
- Ultra Stable Performance
- Capacitance Range:  
0.1pF to 33pF
- Working Voltage: 200V


### ≠ Product Applications

#### Typical Functional Applications:


- Tuning • Bypass • Coupling
- Feedback • D.C. Blocking
- Impedance Matching

#### Typical Circuit Applications:

- UHF/Microwave RF Power Amplifiers
- Mixers • Oscillators • Filter Networks
- Low Noise Amplifiers • Timing Circuits and Delay Lines




### ≠ Part Numbering



### ≠ Capacitor Dimensions

Unit: inch (millimeter)

Code	Term.	Length	Width	Thickness	Overlap
		Lc	Wc	Tc	B
W	Chip	0.040 ± 0.004 (1.02 ± 0.10)	0.020 ± 0.004 (0.51 ± 0.10)	0.020 ± 0.004 (0.51 ± 0.10)	0.010 ± 0.006 (0.25 ± 0.15)



### ≠ Capacitance Tolerance Codes

Code	A	B	C	D	F	G	J	K
Tol.	±0.05pF	±0.1pF	±0.25pF	±0.5pF	±1%	±2%	±5%	±10%



≠ Terminations Type and Code

Termination Code	Termination
W	100% Tin Solder over Nickel Barrier

≠ Voltage Codes

Voltage	Code
50V	500
200V	201
250V	251



≠ 0402N Capacitance Values

For special capacitances, tolerances and WVDC, please contact PPI.

Cap. pF	Cap Code	Tol.	Rated WVDC		Cap. pF	Cap Code	Tol.	Rated WVDC		Cap. pF	Cap Code	Tol.	Rated WVDC	
			Std.	Ext.				Std.	Ext.				Std.	Ext.
0.1	0R1	A,B, C,D	50V or 200V	250V	1.7	1R7	A,B, C,D	50V or 200V	250V	6.8	6R8	A,B, C	50V or 200V	N/A
0.2	0R2				1.8	1R8				7.5	7R5			
0.3	0R3				1.9	1R9				8.2	8R2			
0.4	0R4				2.0	2R0	9.1	9R1						
0.5	0R5				2.1	2R1	10	100	F,G, J,K	50V or 200V	N/A			
0.6	0R6				2.2	2R2		11				110		
0.7	0R7				2.4	2R4		12				120		
0.8	0R8				2.7	2R7		13				130		
0.9	0R9				3.0	3R0		15				150		
1.0	1R0				3.3	3R3		16				160		
1.1	1R1				3.6	3R6	18	180	F,G, J,K	50V or 200V	N/A			
1.2	1R2				3.9	3R9		20				200		
1.3	1R3				4.3	4R3		22				220		
1.4	1R4				4.7	4R7		24				240		
1.5	1R5				5.1	5R1		27				270		
1.6	1R6				5.6	5R6		30				300		
		6.2	6R2	33	330									





### ≠ Electrical Specifications


Quality Factor (Q)	2,000 at 1 MHz min.
Insulation Resistance (IR)	10 <sup>5</sup> Megaohms min. @ +25°C rated WVDC 10 <sup>4</sup> Megaohms min. @ +125°C rated WVDC
Rated Voltage	See Rated Voltage
Dielectric Withstanding Voltage (WVDC)	250% of Rated Voltage of 5 seconds
Operating Temperature Range	-55°C to 175°C
Temperature Coefficient (TC)	0±30ppm/°C
Capacitance Drift	±0.02% or ±0.02pF, whichever is greater
Piezoelectric Effects	None

### ≠ Environmental Specifications


	Specification	Test Parameters
Thermal Shock	No mechanical damage <b>Capacitance Change:</b> ±0.5% or 0.5pF max <b>IR:</b> >10 G Ohms Q>2000 Breakdown Voltage: 2.5x WVDC	MIL-STD-202, Method 107, Condition A. At the maximum rated temperature (-55°C and 175°C) stay 30 minutes, the time of removing shall not be more than 3 minutes. Perform five cycles.
Humidity (Steady State)	No mechanical damage <b>Capacitance Change:</b> ±0.5% or 0.5pF max <b>IR:</b> >1 G Ohms Q>300 Breakdown Voltage: 2.5x WVDC	MIL-STD-202, Method 106
Low Voltage Humidity	No mechanical damage <b>Capacitance Change:</b> ±0.3% or 0.3pF max <b>IR:</b> >1 G Ohms Q>300 Breakdown Voltage: 2.5x WVDC	MIL-STD-202, Method 103, Condition A, with 1.5 Volts DC applied while subjected to an environment of 85°C with 85% relative humidity for 240 hours minimum.
Life	No mechanical damage <b>Capacitance Change:</b> ±2.0% or 0.5pF max <b>IR:</b> >1 G Ohms Q>500 Breakdown Voltage: 2.5x WVDC	MIL-STD-202, Method 108. For 1000 hours, at 175°C. 200% of Voltage for Capacitors
Terminal Adhesion	Termination should not pull off. Ceramic should remain undamaged	Linear pull force exerted on axial leads soldered to each terminal 2.0lbs.
Resistance to Soldering Heat	No mechanical damage <b>Capacitance Change:</b> -1.0%~+2.0% <b>IR:</b> >10 G Ohms Q>500 Breakdown Voltage: 2.5x WVDC	Preheat device to 150°C -180°C for 60 seconds. Dip in 260°C ±5°C solder for 10 ±1 second. Measure after 24± 2 hour cooling period.

Capacitors are designed and manufactured to meet the requirements of MIL-PRF-55681 and MIL-PRF-123.

≠ ESR vs. Frequency



## ≠ First Parallel Resonance




## ≠ Definitions and Measurement Conditions

The **First Parallel Resonance, FPR**, is defined as the lowest frequency at which a suckout or notch appears in  $|S_{21}|$ . It is generally independent of substrate thickness or dielectric constant, but does depend on capacitor orientation. A vertical orientation means the electrode planes are perpendicular to the substrate.

The definitions on the charts are for a capacitor in a series configuration, i.e., mounted across a gap in a microstrip trace with 50-Ohm termination. The measurement conditions are: substrate – Rogers RO4350; substrate dielectric constant = 3.48; substrate thickness (mils) = 10; gap in microstrip trace (mils) = 15; microstrip trace width (mils) = 22; Reference planes at sample edges.

All data has been derived from electrical models created by Modelithics, Inc., a specialty vendor contracted by PPI. The models are derived from measurements on a large number of parts disposed on several different substrates.

## ≠ First Series Resonance



## ≠ Definitions and Measurement Conditions


The **First Series Resonance, FSR**, is defined as the lowest frequency at which the imaginary part of the input impedance,  $\text{Im}[Z_{in}]$ , equals zero. Should  $\text{Im}[Z_{in}]$  or the real part of the input impedance,  $\text{Re}[Z_{in}]$ , not be monotonic with frequency at frequencies lower than those at which  $\text{Im}[Z_{in}] = 0$ , the FSR shall be considered as undefined (represented as a gap in the plot). FSR is dependent on internal capacitor structure; substrate thickness and dielectric constant; capacitor orientation, as defined alongside the FPR plot; and mounting pad dimensions.

The definitions on the charts are for a capacitor in a series configuration, i.e., mounted across a gap in a microstrip trace with 50-Ohm termination. The measurement conditions are: substrate – Rogers RO4350; substrate dielectric constant = 3.48; substrate thickness (mils) = 10; gap in microstrip trace (mils) = 15; microstrip trace width (mils) = 22; Reference planes at sample edges.

All data has been derived from electrical models created by Modelithics, Inc., a specialty vendor contracted by PPI. The models are derived from measurements on a large number of parts disposed on several different substrates.

## ≠ Capacitor Application Program

PPI's brand new online Capacitor Application Program (C.A.P.) helps Engineers and Designers select capacitors according to parameters such as cap value and frequency. C.A.P. allows engineers to insert capacitors requirements (Cap value, Frequency), producing Scattering Matrices (S2P) Charts while providing options (Case Size, Terminations, Mounting), and parameters (ESR, Q, Impedance) along with Datasheets. Once engineers have determined their capacitor requirements, C.A.P. also includes online Requests For Quotes (RFQs) and/or sample requests.



## ≠ Modelithics Vendor Program

PPI offers design engineers a Free 90-Day Trial license for the Modelithics PPI Component Library. This program provides engineers access to extremely accurate scalable simulation models for Passive Plus capacitors with advanced features that enable a more precise and rapid design process.

Microwave Global Models include every part value in a series and permit users to input substrate thickness, dielectric constant, and loss tangent, as well as mounting pad layout dimensions. Selected models also include capacitor orientation – vertical or horizontal – as an input. Engineers can request FREE use of the models by visiting the <https://www.modelithics.com/MVP/PPI>.




## ≠ Recommended Land Pattern Dimensions

Regarding Landing Patterns, please refer to IPC-7351B (table 3-5, 3-6).



**≠ Tape & Reel Specifications** Dimensions: mm

Orientation	Measurement Unit	W	P0	P1	T	F	Minimum Qty per Reel	Std Qty per Reel	Tape Material
H	in.	0.315	0.157	0.079	0.003	0.138	1000	10000	Paper
	mm	8.00	4.00	2.00	0.07	3.50			



$A_0B_0K_0$

- Determined by component size. Typical clearance between the cavity and the component is: .50 (.002) min to .65 (.026) max for 12mm tape.
- The component cannot rotate more than 20° within the determined cavity.

**≠ Engineering Design Kits**

PPI offers Design Kits for engineers who are building and testing prototypes. Each kit contains 16 values; 10 pieces per value.

Kits are 100% RoHS compliant.



Kit Number	Value Range	Values	
DKD0402N01	<b>0.1 - 2.0pF</b>	0.1, 0.2, 0.3, 0.4, 0.5, 0.6, 0.7, 0.8, 0.9, 1.0, 1.2, 1.5, 1.6, 1.8, 2.0pF	
DKD0402N02	<b>1.0 - 10pF</b>	1.0, 1.2, 1.5, 1.8, 2.0, 2.2, 2.4, 2.7, 3.0, 3.3, 3.9, 4.7, 5.6, 6.8, 8.2, 10pF	
DKD0402N03	<b>10 - 33pF</b>	10, 12, 13, 15, 16, 18, 20, 22, 24, 27, 30, 33pF	

**PPI**  
Passive Plus Inc.  
RF & Microwave Components

**DKD0402N01**

**0402N Series 0.1 — 2.0pF**

Size: 0.040" x 0.020"  
TC = NP0 WVDC = 200V

**Hi-Q Low ESR Capacitor Design Kit**

[www.passiveplus.com](http://www.passiveplus.com)

**PPI**  
Passive Plus Inc.  
RF & Microwave Components

**DKD0402N02**

**0402N Series 1.0 — 10pF**

Size: 0.040" x 0.020"  
TC = NP0 WVDC = 200V

**Hi-Q Low ESR Capacitor Design Kit**

[www.passiveplus.com](http://www.passiveplus.com)

**PPI**  
Passive Plus Inc.  
RF & Microwave Components

**DKD0402N03**

**0402N Series 10 — 33pF**

Size: 0.040" x 0.020"  
TC = NP0 WVDC = 200V

**Hi-Q Low ESR Capacitor Design Kit**

[www.passiveplus.com](http://www.passiveplus.com)



≠ **Product Features**

- High Q
- High Power
- Low ESR/ESL
- Low Noise
- High Self-Resonance
- Ultra Stable Performance
- Capacitance Range:  
0.1pF to 100pF
- Working Voltage: 250V


≠ **Product Applications**

**Typical Functional Applications:**


- Tuning • Bypass • Coupling
- Feedback • D.C. Blocking
- Impedance Matching

**Typical Circuit Applications:**

- UHF/Microwave RF Power Amplifiers
- Mixers • Oscillators • Filter Networks
- Low Noise Amplifiers • Timing Circuits and Delay Lines




≠ **Part Numbering**



≠ **Capacitor Dimensions**

Unit: inch (millimeter)

Code	Term.	Length	Width	Thickness	Overlap
		Lc	Wc	Tc	B
W	Chip	0.062 ± 0.006 (1.57 ± 0.15)	0.032 ± 0.006 (0.81 ± 0.15)	0.030 ± 0.005-0.003 (0.76 ± 0.20-0.08)	0.014 ± 0.006 (0.35 ± 0.15)



≠ **Capacitance Tolerance Codes**

Code	A	B	C	D	F	G	J	K
Tol.	±0.05pF	±0.1pF	±0.25pF	±0.5pF	±1%	±2%	±5%	±10%



≠ Terminations Types and Codes

Termination Code	Termination
W	100% Tin Solder over Nickel Barrier
L	90%Tin/10%Lead Solder over Nickel Barrier

≠ Voltage Code

Voltage	Code
250V	251



≠ 0603N Capacitance Values

For special capacitances, tolerances and WVDC, please contact PPI.

Cap. pF	Cap Code	Tol.	Rated WVDC	Cap. pF	Cap Code	Tol.	Rated WVDC	Cap. pF	Cap Code	Tol.	Rated WVDC	Cap. pF	Cap Code	Tol.	Rated WVDC
0.1	0R1			1.7	1R7			6.2	6R2			30	300		
0.2	0R2			1.8	1R8			6.8	6R8			33	330		
0.3	0R3			1.9	1R9			7.5	7R5	A,B,C	250V	36	360		
0.4	0R4			2.0	2R0			8.2	8R2			39	390		
0.5	0R5			2.1	2R1			9.1	9R1			43	430		
0.6	0R6			2.2	2R2			10	100			47	470		
0.7	0R7			2.4	2R4			11	110			51	510	F,G,J,K	250V
0.8	0R8	A,B,C,D	250V	2.7	2R7	A,B,C,D	250V	12	120			56	560		
0.9	0R9			3.0	3R0			13	130			62	620		
1.0	1R0			3.3	3R3			15	150	F,G,J,K	250V	68	680		
1.1	1R1			3.6	3R6			16	160			75	750		
1.2	1R2			3.9	3R9			18	180			82	820		
1.3	1R3			4.3	4R3			20	200			91	910		
1.4	1R4			4.7	4R7			22	220			100	101		
1.5	1R5			5.1	5R1			24	240						
1.6	1R6			5.6	5R6			27	270						





### ⚡ Electrical Specifications

Quality Factor (Q)	2,000 at 1 MHz min.
Insulation Resistance (IR)	10 <sup>5</sup> Megaohms min. @ +25°C rated WVDC 10 <sup>4</sup> Megaohms min. @ +125°C rated WVDC
Rated Voltage	250V
Dielectric Withstanding Voltage (WVDC)	250% of Rated Voltage of 5 seconds
Operating Temperature Range	-55°C to 175°C
Temperature Coefficient (TC)	0±30ppm/°C
Capacitance Drift	±0.02% or ±0.02pF, whichever is greater
Piezoelectric Effects	None


### ⚡ Environmental Specifications

	Specification	Test Parameters
Thermal Shock	No mechanical damage <b>Capacitance Change:</b> ±0.5% or 0.5pF max <b>IR:</b> >10 G Ohms Q>2000 Breakdown Voltage: 2.5x WVDC	MIL-STD-202, Method 107, Condition A. At the maximum rated temperature (-55°C and 175°C) stay 30 minutes, the time of removing shall not be more than 3 minutes. Perform five cycles.
Humidity (Steady State)	No mechanical damage <b>Capacitance Change:</b> ±0.5% or 0.5pF max <b>IR:</b> >1 G Ohms Q>300 Breakdown Voltage: 2.5x WVDC	MIL-STD-202, Method 106
Low Voltage Humidity	No mechanical damage <b>Capacitance Change:</b> ±0.3% or 0.3pF max <b>IR:</b> >1 G Ohms Q>300 Breakdown Voltage: 2.5x WVDC	MIL-STD-202, Method 103, Condition A, with 1.5 Volts DC applied while subjected to an environment of 85°C with 85% relative humidity for 240 hours minimum.
Life	No mechanical damage <b>Capacitance Change:</b> ±2.0% or 0.5pF max <b>IR:</b> >1 G Ohms Q>500 Breakdown Voltage: 2.5x WVDC	MIL-STD-202, Method 108. For 1000 hours, at 175°C. 200% of Voltage for Capacitors
Terminal Adhesion	Termination should not pull off. Ceramic should remain undamaged	Linear pull force exerted on axial leads soldered to each terminal 2.0lbs.
Resistance to Soldering Heat	No mechanical damage <b>Capacitance Change:</b> -1.0%~+2.0% <b>IR:</b> >10 G Ohms Q>500 Breakdown Voltage: 2.5x WVDC	Preheat device to 150°C -180°C for 60 seconds. Dip in 260°C ±5°C solder for 10 ±1 second. Measure after 24± 2 hour cooling period.

Capacitors are designed and manufactured to meet the requirements of MIL-PRF-55681 and MIL-PRF-123.




**⚡ ESR vs. Frequency**



## ≠ First Parallel Resonance

0603N Horizontal First Parallel Resonances (FPR)



## ≠ Definitions and Measurement Conditions


The **First Parallel Resonance**, **FPR**, is defined as the lowest frequency at which a suckout or notch appears in  $|S_{21}|$ . It is generally independent of substrate thickness or dielectric constant, but does depend on capacitor orientation. A vertical orientation means the electrode planes are perpendicular to the substrate.

The definitions on the charts are for a capacitor in a series configuration, i.e., mounted across a gap in a microstrip trace with 50-Ohm termination. The measurement conditions are: substrate – Rogers RT/duriod® 5880; substrate dielectric constant = 2.20; substrate thickness (mils) = 10; gap in microstrip trace (mils) = 23.7; microstrip trace width (mils) = 30.0; Reference planes at sample edges.

All data has been derived from electrical models created by Modelithics, Inc., a specialty vendor contracted by PPI. The models are derived from measurements on a large number of parts disposed on several different substrates.

## ≠ First Series Resonance

0603N Horizontal First Series Resonances (FSR)



## ≠ Definitions and Measurement Conditions


The **First Series Resonance, FSR**, is defined as the lowest frequency at which the imaginary part of the input impedance,  $\text{Im}[Z_{in}]$ , equals zero. Should  $\text{Im}[Z_{in}]$  or the real part of the input impedance,  $\text{Re}[Z_{in}]$ , not be monotonic with frequency at frequencies lower than those at which  $\text{Im}[Z_{in}] = 0$ , the FSR shall be considered as undefined (represented as a gap in the plot). FSR is dependent on internal capacitor structure; substrate thickness and dielectric constant; capacitor orientation, as defined alongside the FPR plot; and mounting pad dimensions.

The definitions on the charts are for a capacitor in a series configuration, i.e., mounted across a gap in a microstrip trace with 50-Ohm termination. The measurement conditions are: substrate – Rogers RT/duriod® 5880; substrate dielectric constant = 2.20; substrate thickness (mils) = 10; gap in microstrip trace (mils) = 23.7; microstrip trace width (mils) = 30.0; Reference planes at sample edges.

All data has been derived from electrical models created by Modelithics, Inc., a specialty vendor contracted by PPI. The models are derived from measurements on a large number of parts disposed on several different substrates.

## ≠ Capacitor Application Program

PPI's brand new online Capacitor Application Program (C.A.P.) helps Engineers and Designers select capacitors according to parameters such as cap value and frequency. C.A.P. allows engineers to insert capacitors requirements (Cap value, Frequency), producing Scattering Matrices (S2P) Charts while providing options (Case Size, Terminations, Mounting), and parameters (ESR, Q, Impedance) along with Datasheets. Once engineers have determined their capacitor requirements, C.A.P. also includes online Requests For Quotes (RFQs) and/or sample requests.



## ≠ Modelithics Vendor Program

PPI offers design engineers a Free 90-Day Trial license for the Modelithics PPI Component Library. This program provides engineers access to extremely accurate scalable simulation models for Passive Plus capacitors with advanced features that enable a more precise and rapid design process.

Microwave Global Models include every part value in a series and permit users to input substrate thickness, dielectric constant, and loss tangent, as well as mounting pad layout dimensions. Selected models also include capacitor orientation – vertical or horizontal – as an input. Engineers can request FREE use of the models by visiting the <https://www.modelithics.com/MVP/PPI>.



## ≠ Recommended Land Pattern Dimensions

Regarding Landing Patterns, please refer to IPC-7351B (table 3-5, 3-6).




EIA Low ESR  
Multi-Layer Ceramic Capacitors

**0603N (0.060" x 0.030")**

**≠ Tape & Reel Specifications** Dimensions: mm

Orientation	Measurement Unit	W	P0	P1	T	F	Minimum Qty per Reel	Std Qty per Reel	Tape Material
H	in. mm	0.315 8.00	0.157 4.00	0.157 4.00	0.004 0.10	0.138 3.50	500	4000	Paper



A<sub>0</sub>B<sub>0</sub>K<sub>0</sub>

- Determined by component size. Typical clearance between the cavity and the component is: .50 (.002) min to .65 (.026) max for 12mm tape.
- The component cannot rotate more than 20° within the determined cavity.

**≠ Engineering Design Kits**

PPI offers Design Kits for engineers who are building and testing prototypes. Each kit contains 16 values; 10 pieces per value.

Kits are 100% RoHS compliant.



Kit Number	Value Range	Values	RoHS
DKD0603N01	0.1 - 2.0pF	0.1, 0.2, 0.3, 0.4, 0.5, 0.6, 0.7, 0.8, 0.9, 1.0, 1.1, 1.2, 1.5, 1.6, 1.8, 2.0pF	✓ RoHS
DKD0603N02	1.0 - 10pF	1.0, 1.2, 1.5, 1.8, 2.0, 2.2, 2.4, 2.7, 3.0, 3.3, 3.9, 4.7, 5.6, 6.8, 8.2, 10pF	✓ RoHS
DKD0603N03	10 - 100pF	10, 12, 15, 18, 20, 22, 24, 27, 30, 33, 39, 47, 56, 68, 100pF	✓ RoHS

**PPI**  
Passive Plus Inc.  
RF & Microwave Components

**DKD0603N01**

**0603N Series 0.1 — 2.0pF**  
Size: 0.060" x 0.030"  
TC = NP0 WVDC = 250V

**Hi-Q Low ESR Capacitor Design Kit**

www.passiveplus.com

**PPI**  
Passive Plus Inc.  
RF & Microwave Components

**DKD0603N02**

**0603N Series 1.0 — 10pF**  
Size: 0.060" x 0.030"  
TC = NP0 WVDC = 250V

**Hi-Q Low ESR Capacitor Design Kit**

www.passiveplus.com

**PPI**  
Passive Plus Inc.  
RF & Microwave Components

**DKD0603N03**

**0603N Series 10 — 100pF**  
Size: 0.060" x 0.030"  
TC = NP0 WVDC = 250V

**Hi-Q Low ESR Capacitor Design Kit**

www.passiveplus.com



### ≠ Product Features

- High Q
- High Power
- Low ESR/ESL
- Low Noise
- High Self-Resonance
- Ultra Stable Performance
- Capacitance Range:  
0.1pF to 100pF
- Working Voltage: 500V


### ≠ Product Applications

#### Typical Functional Applications:


- Tuning • Bypass • Coupling
- Feedback • D.C. Blocking
- Impedance Matching

#### Typical Circuit Applications:

- UHF/Microwave RF Power Amplifiers
- Mixers • Oscillators • Filter Networks
- Low Noise Amplifiers • Timing Circuits and Delay Lines



### ≠ Part Numbering



### ≠ Capacitor Dimensions Unit: inch (millimeter)

Code	Term.	Length	Width	Thickness	Overlap
		Lc	Wc	Tc	B
W	Chip	0.065 ± 0.006 (1.65 ± 0.15)	0.080 ± 0.006 (2.02 ± 0.15)	0.100 ± 0.008 (2.54 ± 0.20)	0.020 ± 0.004 (0.50 ± 0.10)

### ≠ Capacitance Tolerance Codes


Code	B	C	G	J
Tol.	±0.1pF	±0.25pF	±2%	±5%



EIA Low ESR  
Multi-Layer Ceramic Capacitors


**0708N (0.070" x 0.080")**

≠ Terminations Types and Codes

Termination Code	Termination
W 	100% Sn Solder over Nickel Plating
L	90%Sn10%Pb Tin/Lead

≠ Voltage Code

Voltage	Code
500V	501



≠ 0708N Capacitance Values

For special capacitances, tolerances and WVDC, please contact PPI.

Cap. pF	Cap Code	Tol.	Rated WVDC	Cap. pF	Cap Code	Tol.	Rated WVDC	Cap. pF	Cap Code	Tol.	Rated WVDC	Cap. pF	Cap Code	Tol.	Rated WVDC
1.0	1R0			2.7	2R7			10	100			39	390		
1.1	1R1			3.0	3R0			11	110			43	430		
1.2	1R2			3.3	3R3			12	120			47	470		
1.3	1R3			3.6	3R6			13	130			51	510		
1.4	1R4			3.9	3R9			15	150			56	560		
1.5	1R5			4.3	4R3			16	160			62	620	G,J	500V
1.6	1R6	B,C	500V	4.7	4R7	B,C	500V	18	180	G,J	500V	68	680		
1.7	1R7			5.1	5R1			20	200			75	750		
1.8	1R8			5.6	5R6			22	220			82	820		
1.9	1R9			6.2	6R2			24	240			91	910		
2.0	2R0			6.8	6R8			27	270			100	101		
2.1	2R1			7.5	7R5			30	300						
2.2	2R2			8.2	8R2			33	330						
2.4	2R4			9.1	9R1			36	360						





### ≠ Electrical Specifications

Quality Factor (Q)	2,000 at 1 MHz min.
Insulation Resistance (IR)	10 <sup>5</sup> Megaohms min. @ +25°C rated WVDC 10 <sup>4</sup> Megaohms min. @ +125°C rated WVDC
Rated Voltage	500V
Dielectric Withstanding Voltage (WVDC)	250% of Rated Voltage of 5 seconds, Rated Voltage ≤500 VDC
Operating Temperature Range	-55°C to 175°C
Temperature Coefficient (TC)	0±30ppm/°C
Capacitance Drift	±0.02% or ±0.02pF, whichever is greater
Piezoelectric Effects	None


### ≠ Environmental Specifications

	Specification	Test Parameters
Thermal Shock	No mechanical damage <b>Capacitance Change:</b> ±0.5% or 0.5pF max <b>IR:</b> >10 G Ohms Q>500 Breakdown Voltage: 2.5x WVDC	MIL-STD-202, Method 107, Condition A. At the maximum rated temperature (-55°C and 175°C) stay 30 minutes, the time of removing shall not be more than 3 minutes. Perform five cycles.
Humidity (Steady State)	No mechanical damage <b>Capacitance Change:</b> ±0.5% or 0.5pF max <b>IR:</b> >1 G Ohms Q>300 Breakdown Voltage: 2.5x WVDC	MIL-STD-202, Method 106
Low Voltage Humidity	No mechanical damage <b>Capacitance Change:</b> ±0.3% or 0.3pF max <b>IR:</b> >1 G Ohms Q>300 Breakdown Voltage: 2.5x WVDC	MIL-STD-202, Method 103, Condition A, with 1.5 Volts DC applied while subjected to an environment of 85°C with 85% relative humidity for 240 hours minimum.
Life	No mechanical damage <b>Capacitance Change:</b> ±2.0% or 0.5pF max <b>IR:</b> >1 G Ohms Q>500 Breakdown Voltage: 2.5x WVDC	MIL-STD-202, Method 108. For 1000 hours, at 175°C. 200% of Voltage for Capacitors, Rated Voltage ≤ 500VDC
Terminal Adhesion	Termination should not pull off. Ceramic should remain undamaged	Test per MIL-STD-202, Method 211. Terminations for chips withstand a pull of 5lbs min., 15lbs typical, for 5 seconds in direction perpendicular to the termination surface of the capacitor.
Resistance to Soldering Heat	No mechanical damage <b>Capacitance Change:</b> -1.0%~+2.0 <b>IR:</b> >10 G Ohms Q>500 Breakdown Voltage: 2.5x WVDC	Preheat device to 150°C -180°C for 60 seconds. Dip in 260°C ±5°C solder for 10 ±1 second. Measure after 24± 2 hour cooling period.


Capacitors are designed and manufactured to meet the requirements of MIL-PRF-55681 and MIL-PRF-123.

**≠ ESR vs. Frequency**

0708N ESRs for Cap Values ≤ 30 pF




0708N ESRs for Cap Values > 30 pF



## ≠ First Parallel Resonance

0708N FPR, Vertical Orientation



## ≠ Definitions and Measurement Conditions


The **First Parallel Resonance, FPR**, is defined as the lowest frequency at which a suckout or notch appears in  $|S_{21}|$ . It is generally independent of substrate thickness or dielectric constant, but does depend on capacitor orientation. A vertical orientation means the electrode planes are perpendicular to the substrate.

The definitions on the charts are for a capacitor in a series configuration, i.e., mounted across a gap in a microstrip trace with 50-Ohm termination. The measurement conditions are: substrate – Rogers 3003C; substrate dielectric constant = 3.00; substrate thickness (mils) = 40; gap in microstrip trace (mils) = 28; microstrip trace width (mils) = 100; Reference planes at sample edges.

All data has been derived from electrical models created by Modelithics, Inc., a specialty vendor contracted by PPI. The models are derived from measurements on a large number of parts disposed on several different substrates.

## ≠ First Series Resonance

0708N FSR, Vertical Orientation



## ≠ Definitions and Measurement Conditions

The **First Series Resonance, FSR**, is defined as the lowest frequency at which the imaginary part of the input impedance,  $\text{Im}[Z_{in}]$ , equals zero. Should  $\text{Im}[Z_{in}]$  or the real part of the input impedance,  $\text{Re}[Z_{in}]$ , not be monotonic with frequency at frequencies lower than those at which  $\text{Im}[Z_{in}] = 0$ , the FSR shall be considered as undefined (represented as a gap in the plot). FSR is dependent on internal capacitor structure; substrate thickness and dielectric constant; capacitor orientation, as defined alongside the FPR plot; and mounting pad dimensions.


The definitions on the charts are for a capacitor in a series configuration, i.e., mounted across a gap in a microstrip trace with 50-Ohm termination. The measurement conditions are: substrate – Rogers 3003C; substrate dielectric constant = 3.00; substrate thickness (mils) = 40; gap in microstrip trace (mils) = 28; microstrip trace width (mils) = 100; Reference planes at sample edges.

All data has been derived from electrical models created by Modelithics, Inc., a specialty vendor contracted by PPI. The models are derived from measurements on a large number of parts disposed on several different substrates.




**≠ Q vs. Capacitance**

0708N Q for Cap Values ≤ 30 pF




0708N Q for Cap Values > 30 pF



## ≠ Capacitor Application Program

PPI's brand new online Capacitor Application Program (C.A.P.) helps Engineers and Designers select capacitors according to parameters such as cap value and frequency. C.A.P. allows engineers to insert capacitors requirements (Cap value, Frequency), producing Scattering Matrices (S2P) Charts while providing options (Case Size, Terminations, Mounting), and parameters (ESR, Q, Impedance) along with Datasheets. Once engineers have determined their capacitor requirements, C.A.P. also includes online Requests For Quotes (RFQs) and/or sample requests.



## ≠ Modelithics Vendor Program

PPI offers design engineers a Free 90-Day Trial license for the Modelithics PPI Component Library. This program provides engineers access to extremely accurate scalable simulation models for Passive Plus capacitors with advanced features that enable a more precise and rapid design process.

Microwave Global Models include every part value in a series and permit users to input substrate thickness, dielectric constant, and loss tangent, as well as mounting pad layout dimensions. Selected models also include capacitor orientation – vertical or horizontal – as an input. Engineers can request FREE use of the models by visiting the <https://www.modelithics.com/MVP/PPI>.



## ≠ Recommended Land Pattern Dimensions

Regarding Landing Patterns, please refer to IPC-7351B (table 3-5, 3-6).




EIA Low ESR  
Multi-Layer Ceramic Capacitors

**0708N (0.070" x 0.080")**

### ≠ Tape & Reel Specifications – Vertical Orientation

Orientation	Measurement Unit	W	P0	P1	T	F	Minimum Qty per Reel	Std Qty per Reel	Tape Material
V	in. mm	0.472 12.00	0.157 4.00	0.157 4.00	0.012 0.30	0.217 5.50	500	1500	Plastic



A<sub>0</sub>B<sub>0</sub>K<sub>0</sub>

- Determined by component size. Typical clearance between the cavity and the component is: .50 (.002) min to .65 (.026) max for 12mm tape.
- The component cannot rotate more than 20° within the determined cavity.

### ≠ Engineering Design Kits

PPI offers Design Kits for engineers who are building and testing prototypes. Each kit contains 16 values; 10 pieces per value.

Kits are 100% RoHS compliant.



Kit Number	Value Range	Values	RoHS
DKD0708N01	1.0 - 10pF	1.0, 1.2, 1.5, 1.8, 2.0, 2.2, 2.4, 2.7, 3.0, 3.3, 3.9, 4.7, 5.6, 6.8, 8.2, 10pF	
DKD0708N02	10 - 100pF	10, 12, 15, 18, 20, 22, 24, 27, 30, 33, 39, 47, 56, 68, 82, 100pF	

DKD0708N01

0708N Series 1.0 — 10pF

Size: 0.070" x 0.080"  
TC = NP0 WVDC = 500V

Hi-Q Low ESR Capacitor Design Kit

www.passiveplus.com

DKD0708N02

0708N Series 10 — 100pF

Size: 0.070" x 0.080"  
TC = NP0 WVDC = 500V

Hi-Q Low ESR Capacitor Design Kit

www.passiveplus.com



**≠ Product Features**

- High Q
- High Power
- Low ESR/ESL
- Low Noise
- High Self-Resonance
- Ultra Stable Performance
- Capacitance Range:  
0.1pF to 220pF
- Working Voltage: 250V

**≠ Product Applications**

**Typical Functional Applications:**

- Tuning • Bypass • Coupling
- Feedback • D.C. Blocking
- Impedance Matching


**Typical Circuit Applications:**

- UHF/Microwave RF Power Amplifiers
- Mixers • Oscillators • Filter Networks
- Low Noise Amplifiers • Timing Circuits and Delay Lines




Marking shown for illustration purposes only. Actual marking may differ.

**≠ Part Numbering**



**≠ Capacitor Dimensions** Unit: inch (millimeter)

Code	Term.	Length	Width	Thickness	Overlap
		Lc	Wc	Tc	B
W	Chip	0.080 ± 0.008 (2.03±0.20)	0.050 ± 0.008 (1.27 ±0.20)	0.040±0.006 (1.02±0.15)	0.020±0.010 (0.50±0.25)




**≠ Capacitance Tolerance Codes**

Code	A	B	C	D	F	G	J	K
Tol.	±0.05pF	±0.1pF	±0.25pF	±0.5pF	±1%	±2%	±5%	±10%




≠ Terminations Types and Codes

Termination Code	Termination
W 	100% Tin Solder over Nickel Barrier
L	90%Tin/10%Lead Solder over Nickel Barrier

≠ Voltage Code

Voltage	Code
250V	251



≠ 0805N Capacitance Values

For special capacitances, tolerances and WVDC, please contact PPI.

Cap. pF	Cap Code	Tol.	Rated WVDC	Cap. pF	Cap Code	Tol.	Rated WVDC	Cap. pF	Cap Code	Tol.	Rated WVDC	Cap. pF	Cap Code	Tol.	Rated WVDC	
0.1	OR1		250V	2.1	2R1	A,B, C,D	250V	13	130	F,G, J,K	250V	91	910	F,G,J,K	250V	
0.2	OR2			2.2	2R2				15			150	100			101
0.3	OR3			2.4	2R4				16			160	110			111
0.4	OR4			2.7	2R7				18			180	120			121
0.5	OR5			3.0	3R0				20			200	130			131
0.6	OR6			3.3	3R3				22			220	150			151
0.7	OR7			3.6	3R6				24			240	160			161
0.8	OR8			3.9	3R9				27			270	180			181
0.9	OR9			4.3	4R3				30			300	200			201
1.0	1R0	A,B, C,D		4.7	4R7				33			330	220			221
1.1	1R1		5.1	5R1		36	360									
1.2	1R2		5.6	5R6		39	390									
1.3	1R3		6.2	6R2		43	430									
1.4	1R4		6.8	6R8		47	470									
1.5	1R5		7.5	7R5	B,C	51	510									
1.6	1R6		8.2	8R2		56	560									
1.7	1R7		9.1	9R1		62	620									
1.8	1R8		10	100	F,G, J,K	68	680									
1.9	1R9		11	110		75	750									
2.0	2R0		12	120		82	820									



## ≠ Electrical Specifications

Quality Factor (Q)	2,000 at 1 MHz min.
Insulation Resistance (IR)	10 <sup>5</sup> Megaohms min. @ +25°C rated WVDC 10 <sup>4</sup> Megaohms min. @ +125°C rated WVDC
Rated Voltage	250V
Dielectric Withstanding Voltage (WVDC)	250% of Rated Voltage of 5 seconds
Operating Temperature Range	-55°C to 175°C
Temperature Coefficient (TC)	0±30ppm/°C
Capacitance Drift	±0.02% or ±0.02pF, whichever is greater
Piezoelectric Effects	None

## ≠ Environmental Specifications

	Specification	Test Parameters
Thermal Shock	No mechanical damage <b>Capacitance Change:</b> ±0.5% or 0.5pF max <b>IR:</b> >10 G Ohms Q>2000 Breakdown Voltage: 2.5x WVDC	MIL-STD-202, Method 107, Condition A. At the maximum rated temperature (-55°C and 175°C) stay 30 minutes, the time of removing shall not be more than 3 minutes. Perform five cycles.
Humidity (Steady State)	No mechanical damage <b>Capacitance Change:</b> ±0.5% or 0.5pF max <b>IR:</b> >1 G Ohms Q>300 Breakdown Voltage: 2.5x WVDC	MIL-STD-202, Method 106
Life	No mechanical damage <b>Capacitance Change:</b> ±2.0% or 0.5pF max <b>IR:</b> >1 G Ohms Q>500 Breakdown Voltage: 2.5x WVDC	MIL-STD-202, Method 108. For 1000 hours, at 175°C. 200% of Voltage for Capacitors, Rated Voltage ≤ 500VDC; 120% of Voltage for Capacitors, 500VDC < Rated Voltage ≤ 1250VDC; 100% for Voltage for Capacitors, Rated Voltage > 1250VDC
Terminal Adhesion	Termination should not pull off. Ceramic should remain undamaged	Linear pull force exerted on axial leads soldered to each terminal. 2.0lbs.
Resistance to Soldering Heat	No mechanical damage <b>Capacitance Change:</b> -1.0%~+2.0% <b>IR:</b> >10 G Ohms Q>500 Breakdown Voltage: 2.5x WVDC	Preheat device to 150°C -180°C for 60 seconds. Dip in 260°C ±5°C solder for 10 ±1 second. Measure after 24± 2 hour cooling period.


Capacitors are designed and manufactured to meet the requirements of MIL-PRF-55681 and MIL-PRF-123.




EIA Low ESR  
Multi-Layer Ceramic Capacitors

**0805N (0.080" x 0.050")**

**≠ ESR vs. Frequency 3.9pF to 100pF**



## ≠ First Parallel Resonance




## ≠ Definitions and Measurement Conditions

The **First Parallel Resonance, FPR**, is defined as the lowest frequency at which a suckout or notch appears in  $|S_{21}|$ . It is generally independent of substrate thickness or dielectric constant, but does depend on capacitor orientation. A horizontal orientation means the capacitor electrode planes are parallel to the plane of the substrate; a vertical orientation means the electrode planes are perpendicular to the substrate.

The definitions on the charts are for a capacitor in a series configuration, i.e., mounted across a gap in a microstrip trace with 50-Ohm termination. The measurement conditions are: substrate – Rogers RO3003; substrate dielectric constant = 3.00; substrate thickness (mils) = 23; gap in microstrip trace (mils) = 23.6; microstrip trace width (mils) = 57.1; Reference planes at sample edges.

All data has been derived from electrical models created by Modelithics, Inc., a specialty vendor contracted by PPI. The models are derived from measurements on a large number of parts disposed on several different substrates.

## ≠ First Series Resonance



## ≠ Definitions and Measurement Conditions


The **First Series Resonance, FSR**, is defined as the lowest frequency at which the imaginary part of the input impedance,  $\text{Im}[Z_{in}]$ , equals zero. Should  $\text{Im}[Z_{in}]$  or the real part of the input impedance,  $\text{Re}[Z_{in}]$ , not be monotonic with frequency at frequencies lower than those at which  $\text{Im}[Z_{in}] = 0$ , the FSR shall be considered as undefined (represented as a gap in the plot). FSR is dependent on internal capacitor structure; substrate thickness and dielectric constant; capacitor orientation, as defined alongside the FPR plot; and mounting pad dimensions.

The definitions on the charts are for a capacitor in a series configuration, i.e., mounted across a gap in a microstrip trace with 50-Ohm termination. The measurement conditions are: substrate – Rogers RO3003; substrate dielectric constant = 3.00; substrate thickness (mils) = 23; gap in microstrip trace (mils) = 23.6; microstrip trace width (mils) = 57.1; Reference planes at sample edges.

All data has been derived from electrical models created by Modelithics, Inc., a specialty vendor contracted by PPI. The models are derived from measurements on a large number of parts disposed on several different substrates.

## ≠ Capacitor Application Program

PPI's brand new online Capacitor Application Program (C.A.P.) helps Engineers and Designers select capacitors according to parameters such as cap value and frequency. C.A.P. allows engineers to insert capacitors requirements (Cap value, Frequency), producing Scattering Matrices (S2P) Charts while providing options (Case Size, Terminations, Mounting), and parameters (ESR, Q, Impedance) along with Datasheets. Once engineers have determined their capacitor requirements, C.A.P. also includes online Requests For Quotes (RFQs) and/or sample requests.



## ≠ Modelithics Vendor Program

PPI offers design engineers a Free 90-Day Trial license for the Modelithics PPI Component Library. This program provides engineers access to extremely accurate scalable simulation models for Passive Plus capacitors with advanced features that enable a more precise and rapid design process.

Microwave Global Models include every part value in a series and permit users to input substrate thickness, dielectric constant, and loss tangent, as well as mounting pad layout dimensions. Selected models also include capacitor orientation – vertical or horizontal – as an input. Engineers can request FREE use of the models by visiting the <https://www.modelithics.com/MVP/PPI>.



## ≠ Recommended Land Pattern Dimensions

Regarding Landing Patterns, please refer to IPC-7351B (table 3-5, 3-6).




EIA Low ESR  
Multi-Layer Ceramic Capacitors

**0805N (0.080" x 0.050")**

**≠ Tape & Reel Specifications** Dimensions: mm



Orientation	Measurement Unit	W	P0	P1	T	F	Minimum Qty per Reel	Std Qty per Reel	Tape Material
H	in.	0.315	0.157	0.157	0.009	0.138	500	3000	Plastic
	mm	8.00	4.00	4.00	0.22	3.50			
V	in.	0.315	0.157	0.157	0.009	0.138	500	1000	Plastic
	mm	8.00	4.00	4.00	0.22	3.50			



A<sub>0</sub>B<sub>0</sub>K<sub>0</sub>

- Determined by component size. Typical clearance between the cavity and the component is: .50 (.002) min to .65 (.026) max for 12mm tape.
- The component cannot rotate more than 20° within the determined cavity.

**≠ Engineering Design Kits**

PPI offers Design Kits for engineers who are building and testing prototypes. Each kit contains 16 values; 10 pieces per value.

Kits are 100% RoHS compliant.



Kit Number	Value Range	Values	RoHS
DKD0805N01	0.1 - 2.0pF	0.1, 0.2, 0.3, 0.4, 0.5, 0.6, 0.7, 0.8, 0.9, 1.0, 1.2, 1.5, 1.6, 1.8, 2.0pF	✓
DKD0805N02	1.0 - 10pF	1.0, 1.2, 1.5, 1.8, 2.0, 2.2, 2.4, 2.7, 3.0, 3.3, 3.9, 4.7, 5.6, 6.8, 8.2, 10pF	✓
DKD0805N03	10 - 100pF	10, 12, 15, 18, 20, 22, 24, 27, 30, 33, 39, 47, 56, 68, 82, 100pF	✓
DKD0805N04	10 - 220pF	10, 15, 18, 20, 24, 27, 30, 39, 47, 56, 68, 82, 100, 120, 150, 180, 220pF	✓

**PPI** Passive Plus Inc.  
RF & Microwave Components

**DKD0805N01**

**0805N Series 0.1 — 2.0pF**

Size: 0.080" x 0.050"  
TC = NP0 WVDC = 250V

Hi-Q Low ESR Capacitor Design Kit

www.passiveplus.com

**PPI** Passive Plus Inc.  
RF & Microwave Components

**DKD0805N02**

**0805N Series 1.0 — 10pF**

Size: 0.080" x 0.050"  
TC = NP0 WVDC = 250V

Hi-Q Low ESR Capacitor Design Kit

www.passiveplus.com

**PPI** Passive Plus Inc.  
RF & Microwave Components

**DKD0805N03**

**0805N Series 10 — 100pF**

Size: 0.080" x 0.050"  
TC = NP0 WVDC = 250V

Hi-Q Low ESR Capacitor Design Kit

www.passiveplus.com

**PPI** Passive Plus Inc.  
RF & Microwave Components

**DKD0805N04**

**0805N Series 10 — 220pF**

Size: 0.080" x 0.050"  
TC = NP0 WVDC = 250V

Hi-Q Low ESR Capacitor Design Kit

www.passiveplus.com



**≠ Product Features**

- High Q
- High Power
- Low ESR/ESL
- Low Noise
- High Self-Resonance
- Ultra Stable Performance
- Capacitance Range:  
0.2pF to 1000pF
- Working Voltage: 500V


**≠ Product Applications**

**Typical Functional Applications:**

- Tuning • Bypass • Coupling
- Feedback • D.C. Blocking
- Impedance Matching


**Typical Circuit Applications:**

- UHF/Microwave RF Power Amplifiers
- Mixers • Oscillators • Filter Networks
- Low Noise Amplifiers • Timing Circuits and Delay Lines




Marking shown for illustration purposes only. Actual marking may differ.

**≠ Part Numbering**



**≠ Capacitor Dimensions** Unit: inch (mm)

Code	Length		Width Wc	Thickness Tc	Overlap B
	Lc				
W Chip	0.11	+0.020 -0.010	0.110 ± 0.015	0.10 max	0.015 max
	(2.79	+0.51 -0.25)			



**≠ Capacitance Tolerance Codes**

Code	A	B	C	D	F	G	J	K
Tol.	±0.05pF	±0.1pF	±0.25pF	±0.5pF	±1%	±2%	±5%	±10%






≠ Terminations Types and Codes

Termination Code	Termination
W	100% Tin Solder over Nickel Barrier
L	90%Tin/10%Lead Solder over Nickel Barrier

≠ Voltage Code

Voltage	Code
100V	101
200V	201
500V	501
1000V	102



Marking shown for illustration purposes only.  
Actual marking may differ.

≠ 1111N Capacitance Values

For special capacitances, tolerances and WVDC, please contact PPI.

Cap. pF	Cap Code	Tol.	Rated WVDC		Cap. pF	Cap Code	Tol.	Rated WVDC		Cap. pF	Cap Code	Tol.	Rated WVDC		Cap. pF	Cap Code	Tol.	Rated WVDC	
			Std.	Ext.				Std.	Ext.				Std.	Ext.				Std.	Ext.
0.2	0R2	A,B, C,D	500V	1000V	2.7	2R7	A,B, C,D	500V	1000V	22	220	F,G, J,K	500V	1000V	180	181	F,G, J,K	500V	1000V
0.3	0R3				3.0	3R0				24	240				200	201			
0.4	0R4				3.3	3R3				27	270				220	221			
0.5	0R5				3.6	3R6				30	300				240	241			
0.6	0R6				3.9	3R9				33	330				270	271			
0.7	0R7				4.3	4R3				36	360				300	301			
0.8	0R8				4.7	4R7				39	390				330	331			
0.9	0R9				5.1	5R1				43	430				360	361			
1.0	1R0				5.6	5R6				47	470				390	391			
1.1	1R1				6.2	6R2				51	510				430	431			
1.2	1R2				6.8	6R8				56	560				470	471			
1.3	1R3				7.5	7R5				62	620				510	511			
1.4	1R4				8.2	8R2				68	680				560	561			
1.5	1R5				9.1	9R1				75	750				620	621			
1.6	1R6				10	100				82	820				680	681			
1.7	1R7				11	110				91	910				750	751			
1.8	1R8				12	120				100	101				820	821			
1.9	1R9				13	130				110	111				910	911			
2.0	2R0				15	150				120	121				1000	102			
2.1	2R1	16	160	130	131														
2.2	2R2	18	180	150	151														
2.4	2R4	20	200	160	161														



## ≠ Electrical Specifications



Quality Factor (Q)	2,000 at 1 MHz min.
Insulation Resistance (IR)	10 <sup>5</sup> Megaohms min. @ +25°C rated WVDC 10 <sup>4</sup> Megaohms min. @ +125°C rated WVDC
Rated Voltage	See Rated Voltage Table
Dielectric Withstanding Voltage (WVDC)	250% of Rated Voltage of 5 seconds, Rated Voltage ≤ 500VDC 150% of Voltage for 5 seconds, 500VDC < Rated Voltage ≤ 1250 VDC 120% of Voltage for 5 seconds, Rated Voltage > 1250 VDC
Operating Temperature Range	-55°C to 175°C
Temperature Coefficient (TC)	0±30ppm/°C
Capacitance Drift	±0.02% or ±0.02pF, whichever is greater
Piezoelectric Effects	None

## ≠ Environmental Specifications


	Specification	Test Parameters
Thermal Shock	No mechanical damage <b>Capacitance Change:</b> ±0.5% or 0.5pF max <b>IR:</b> >1 G Ohms Q>500	MIL-STD-202, Method 107, Condition A. At the maximum rated temperature (-55°C and 175°C) stay 30 minutes, the time of removing shall not be more than 3 minutes. Perform five cycles.
Moisture Resistance	Breakdown Voltage: 2.5x WVDC	MIL-STD-202, Method 106
Humidity (Steady State)	No mechanical damage <b>Capacitance Change:</b> ±0.5% or 0.5pF max <b>IR:</b> >1 G Ohms Q>300 Breakdown Voltage: 2.5x WVDC	MIL-STD-202, Method 103, Condition A With 1.5Volts DC applied while subjected to an environment of 85°C with 85% relative humidity for 240 hours minimum.
Life	No mechanical damage <b>Capacitance Change:</b> ±2.0% or 0.5pF max <b>IR:</b> >1 G Ohms Q>500 Breakdown Voltage: 2.5x WVDC	MIL-STD-202, Method 108. For 1000 hours, at 175°C. 200% of Voltage for Capacitors, Rated Voltage ≤ 500VDC; 120% of Voltage for Capacitors, 500VDC < Rated Voltage ≤ 1250VDC; 100% for Voltage for Capacitors, Rated Voltage > 1250VDC
Terminal Adhesion	Termination should not pull off. Ceramic should remain undamaged	Linear pull force exerted on axial leads soldered to each terminal. 2.0lbs.
Resistance to Soldering Heat	No mechanical damage <b>Capacitance Change:</b> -1.0%~+2.0 <b>IR:</b> >1 G Ohms Q>500 Breakdown Voltage: 2.5x WVDC	Preheat device to 150°C -180°C for 60 seconds. Dip in 260°C ±5C solder for 10 ±1 second. Measure after 24± 2 hour cooling period.

Capacitors are designed and manufactured to meet the requirements of MIL-PRF-55681 and MIL-PRF-123.

**⚡ ESR vs. Frequency**



## ≠ First Parallel Resonance




## ≠ Definitions and Measurement Conditions

The **First Parallel Resonance, FPR**, is defined as the lowest frequency at which a suckout or notch appears in  $|S_{21}|$ . It is generally independent of substrate thickness or dielectric constant, but does depend on capacitor orientation. A horizontal orientation means the capacitor electrode planes are parallel to the plane of the substrate; a vertical orientation means the electrode planes are perpendicular to the substrate.

The definitions on the carts are for a capacitor in a series configuration, i.e., mounted across a gap in a microstrip trace with a 50-Ohm termination. The measurement conditions are: substrate – Rogers RO4350; substrate dielectric constant = 3.48; horizontal mount substrate thickness (mils) = 55; vertical mount substrate thickness (mils) = 45; gap in microstrip trace (mils) = 61.1; horizontal mount microstrip trace width (mils) = 123.7; vertical mount microstrip trace width (mils) = 101.0. Reference planes at sample edges.

All data has been derived from electrical models created by Modelithics, Inc., a specialty vendor contracted by PPI. The models are derived from measurements on a large number of parts disposed on several different substrates.

## ≠ First Series Resonance



## ≠ Definitions and Measurement Conditions


The **First Series Resonance, FSR**, is defined as the lowest frequency at which the imaginary part of the input impedance,  $\text{Im}[Z_{in}]$ , equals zero. Should  $\text{Im}[Z_{in}]$  or the real part of the input impedance,  $\text{Re}[Z_{in}]$ , not be monotonic with frequency at frequencies lower than those at which  $\text{Im}[Z_{in}] = 0$ , the FSR shall be considered as undefined (represented as a gap in the plot). FSR is dependent on internal capacitor structure; substrate thickness and dielectric constant; capacitor orientation, as defined alongside the FPR plot; and mounting pad dimensions.

The definitions on the carts are for a capacitor in a series configuration, i.e., mounted across a gap in a microstrip trace with a 50-Ohm termination. The measurement conditions are: substrate – Rogers RO4350; substrate dielectric constant = 3.48; horizontal mount substrate thickness (mils) = 55; vertical mount substrate thickness (mils) = 45; gap in microstrip trace (mils) = 61.1; horizontal mount microstrip trace width (mils) = 123.7; vertical mount microstrip trace width (mils) = 101.0. Reference planes at sample edges.

All data has been derived from electrical models created by Modelithics, Inc., a specialty vendor contracted by PPI. The models are derived from measurements on a large number of parts disposed on several different substrates.

## ≠ Capacitor Application Program

PPI's brand new online Capacitor Application Program (C.A.P.) helps Engineers and Designers select capacitors according to parameters such as cap value and frequency. C.A.P. allows engineers to insert capacitors requirements (Cap value, Frequency), producing Scattering Matrices (S2P) Charts while providing options (Case Size, Terminations, Mounting), and parameters (ESR, Q, Impedance) along with Datasheets. Once engineers have determined their capacitor requirements, C.A.P. also includes online Requests For Quotes (RFQs) and/or sample requests.



## ≠ Modelithics Vendor Program

PPI offers design engineers a Free 90-Day Trial license for the Modelithics PPI Component Library. This program provides engineers access to extremely accurate scalable simulation models for Passive Plus capacitors with advanced features that enable a more precise and rapid design process.

Microwave Global Models include every part value in a series and permit users to input substrate thickness, dielectric constant, and loss tangent, as well as mounting pad layout dimensions. Selected models also include capacitor orientation – vertical or horizontal – as an input. Engineers can request FREE use of the models by visiting the <https://www.modelithics.com/MVP/PPI>.



## ≠ Recommended Land Pattern Dimensions


Regarding Landing Patterns, please refer to IPC-7351B (table 3-5, 3-6).



### ≠ Tape & Reel Specifications



Orientation	Measurement Unit	W	P0	P1	T	F	Minimum Qty per Reel	Std Qty per Reel	Tape Material
H	in.	0.315	0.157	0.157	0.010	0.138	500	2000	Plastic
	mm	8.00	4.00	4.00	0.25	3.50			
V	in.	0.472	0.157	0.157	0.016	0.217	500	1500	
	mm	12.00	4.00	4.00	0.40	5.50			



A<sub>0</sub>B<sub>0</sub>K<sub>0</sub>

- Determined by component size. Typical clearance between the cavity and the component is: .50 (.002) min to .65 (.026) max for 12mm tape.
- The component cannot rotate more than 20° within the determined cavity.

### ≠ Engineering Design Kits

PPI offers Design Kits for engineers who are building and testing prototypes. Each kit contains 16 values; 10 pieces per value.

Kits are 100% RoHS compliant.



Kit Number	Value Range	Values	RoHS
DKD1111N01	1.0 - 10pF	1.0, 1.2, 1.5, 1.8, 2.0, 2.2, 2.4, 2.7, 3.0, 3.3, 3.9, 4.7, 5.6, 6.8, 8.2, 10pF	✓
DKD1111N02	10 - 100pF	10, 12, 15, 18, 20, 22, 24, 27, 30, 33, 39, 47, 56, 68, 82, 100pF	✓
DKD1111N03	100 - 1000pF	100, 120, 150, 180, 200, 220, 240, 270, 300, 330, 390, 470, 560, 680, 820, 1000pF	✓

**PPI**  
Passive Plus Inc.  
RF & Microwave Components

DKD1111N01

**1111N Series 1.0 — 10pF**

Size: 0.110" x 0.110"  
TC = NP0 WVDC = 500V

**Hi-Q Low ESR Capacitor Design Kit**

www.passiveplus.com

**PPI**  
Passive Plus Inc.  
RF & Microwave Components

DKD1111N02

**1111N Series 10 — 100pF**

Size: 0.110" x 0.110"  
TC = NP0 WVDC = 500V

**Hi-Q Low ESR Capacitor Design Kit**

www.passiveplus.com

**PPI**  
Passive Plus Inc.  
RF & Microwave Components

DKD1111N03

**1111N Series 100 — 1000pF**

Size: 0.110" x 0.110"  
TC = NP0 WVDC = 500V

**Hi-Q Low ESR Capacitor Design Kit**

www.passiveplus.com



# Standard Design Kits

**PPI**  
Passive Plus Inc.  
RF & Microwave Components

**DKD0201N01**

**0201N Series 0.1 — 2.0pF**  
Size: 0.020" x 0.010"  
TC = NP0 WVDC = 50V

Hi-Q Low ESR Capacitor Design Kit

www.passiveplus.com

**PPI**  
Passive Plus Inc.  
RF & Microwave Components

**DKD0402N01**

**0402N Series 0.1 — 2.0pF**  
Size: 0.040" x 0.020"  
TC = NP0 WVDC = 200V

Hi-Q Low ESR Capacitor Design Kit

www.passiveplus.com

**PPI**  
Passive Plus Inc.  
RF & Microwave Components

**DKD0603N01**

**0603N Series 0.1 — 2.0pF**  
Size: 0.060" x 0.030"  
TC = NP0 WVDC = 250V

Hi-Q Low ESR Capacitor Design Kit

www.passiveplus.com

**PPI**  
Passive Plus Inc.  
RF & Microwave Components

**DKD0708N01**

**0708N Series 1.0 — 10pF**  
Size: 0.070" x 0.080"  
TC = NP0 WVDC = 500V

Hi-Q Low ESR Capacitor Design Kit

www.passiveplus.com

**PPI**  
Passive Plus Inc.  
RF & Microwave Components

**DKD0805N01**

**0805N Series 0.1 — 2.0pF**  
Size: 0.080" x 0.050"  
TC = NP0 WVDC = 250V

Hi-Q Low ESR Capacitor Design Kit

www.passiveplus.com

**PPI**  
Passive Plus Inc.  
RF & Microwave Components

**DKD1111N01**

**1111N Series 1.0 — 10pF**  
Size: 0.110" x 0.110"  
TC = NP0 WVDC = 500V

Hi-Q Low ESR Capacitor Design Kit

www.passiveplus.com

**PPI**  
Passive Plus Inc.  
RF & Microwave Components

**DKD0505C01**

**0505C Series 0.1 — 2.0pF**  
Size: 0.055" x 0.055"  
TC = NP0 WVDC = 150V

Hi-Q Low ESR Capacitor Design Kit

www.passiveplus.com

**PPI**  
Passive Plus Inc.  
RF & Microwave Components

**DKD1111C01**

**1111C Series 1.0 — 10pF**  
Size: 0.110" x 0.110"  
TC = NP0 WVDC = 500V

Hi-Q Low ESR Capacitor Design Kit

www.passiveplus.com

**PPI**  
Passive Plus Inc.  
RF & Microwave Components

**DKD0505P01**

**0505P Series 0.1 — 2.0pF**  
Size: 0.055" x 0.055"  
TC = P90 WVDC = 150V

Hi-Q Low ESR Capacitor Design Kit

www.passiveplus.com



0505 & 1111 case size kits  
are available in  
Magnetic & Non-Magnetic  
Terminations

**PPI**  
Passive Plus Inc.  
RF & Microwave Components

**DKD1111P01**

**1111P Series 1.0 — 10pF**  
Size: 0.110" x 0.110"  
TC = P90 WVDC = 500V

Hi-Q Low ESR Capacitor Design Kit

www.passiveplus.com



**≠ High Q Capacitor Design Kits**

According to the customer’s demand, PPI can provide many kinds of tool kits for engineers to design and debug the circuit. All of our products satisfy the requirement of RoHS instruction.



PPI also offers kits for Non-Magnetic MRI applications. Engineering design kits are also available in multiple sizes as well. All kits are RoHS Compliant.

Standard Values updated in 2022.

Kit Number		Value Range	Values
Magnetic	Non-Magnetic		
DKD0505C01	DKD0505C05	<b>0.1 - 2.0pF</b>	0.1, 0.2, 0.3, 0.4, 0.5, 0.6, 0.7, 0.8, 0.9, 1.0, 1.2, 1.5, 1.6, 1.8, 2.0pF
DKD0505P01	DKD0505P05		
DKD0505C02	DKD0505C06	<b>1 - 10pF</b>	1.0, 1.2, 1.5, 1.8, 2.0, 2.2, 2.4, 2.7, 3.0, 3.3, 3.9, 4.7, 5.6, 6.8, 8.2, 10pF
DKD0505P02	DKD0505P06		
DKD0505C03	DKD0505C07	<b>10 - 100pF</b>	10, 12, 15, 18, 20, 22, 24, 27, 30, 33, 39, 47, 56, 68, 82, 100pF
DKD0505P03	DKD0505P07		
DKD0505C04	DKD0505C08	<b>100 - 1000pF</b>	100, 120, 150, 180, 200, 220, 240, 270, 300, 330, 390, 470, 560, 680, 820, 1000pF
DKD1111C01	DKD1111C05	<b>1.0 - 10pF</b>	1.0, 1.2, 1.5, 1.8, 2.0, 2.2, 2.4, 2.7, 3.0, 3.3, 3.9, 4.7, 5.6, 6.8, 8.2, 10pF
DKD1111P01	DKD1111P05		
DKD1111C02	DKD1111C06	<b>10 - 100pF</b>	10, 12, 15, 18, 20, 22, 24, 27, 30, 33, 39, 47, 56, 68, 82, 100pF
DKD1111P02	DKD1111P06		
DKD1111C03	DKD1111C07	<b>100 - 1000pF</b>	100, 120, 150, 180, 200, 220, 240, 270, 300, 330, 390, 470, 560, 680, 820, 1000pF
DKD1111P03	DKD1111P07		
DKD1111C04	DKD1111C08	<b>1000 - 10000pF</b>	1000, 1100, 1200, 1500, 1800, 2000, 2200, 2700, 3000, 3300, 3900, 4700, 5100, 5600, 10000pF
DKD1111P04	DKD1111P08		

**⚡ EIA Low ESR Design Kits**

<b>Kit Number</b>	<b>Value Range</b>	<b>Values</b>
DKD0201N01	<b>0.1 - 2.0pF</b>	0.1, 0.2, 0.3, 0.5, 0.7, 0.8, 0.9, 1.0, 1.3, 1.5, 1.7, 1.9, 2.0pF
DKD0201N02	<b>1.0 - 10pF</b>	1.0, 1.3, 1.5, 1.7, 1.9, 2.0, 2.2, 2.7, 3.0, 3.9, 4.7, 5.6, 6.8, 7.5, 8.2, 10pF
DKD0201N03	<b>10 - 47pF</b>	10, 13, 15, 18, 20, 22, 27, 30, 39, 47pF
DKD0402N01	<b>0.1 - 2.0pF</b>	0.1, 0.2, 0.3, 0.4, 0.5, 0.6, 0.7, 0.8, 0.9, 1.0, 1.2, 1.5, 1.6, 1.8, 2.0pF
DKD0402N02	<b>1.0 - 10pF</b>	1.0, 1.2, 1.5, 1.8, 2.0, 2.2, 2.4, 2.7, 3.0, 3.3, 3.9, 4.7, 5.6, 6.8, 8.2, 10pF
DKD0402N03	<b>10 - 33pF</b>	10, 12, 13, 15, 16, 18, 20, 22, 24, 27, 30, 33pF
DKD0603N01	<b>0.1 - 2.0pF</b>	0.1, 0.2, 0.3, 0.4, 0.5, 0.6, 0.7, 0.8, 0.9, 1.0, 1.1, 1.2, 1.5, 1.6, 1.8, 2.0pF
DKD0603N02	<b>1.0 - 10pF</b>	1.0, 1.2, 1.5, 1.8, 2.0, 2.2, 2.4, 2.7, 3.0, 3.3, 3.9, 4.7, 5.6, 6.8, 8.2, 10pF
DKD0603N03	<b>10 - 100pF</b>	10, 12, 15, 18, 20, 22, 24, 27, 30, 33, 39, 47, 56, 68, 100pF
DKD0708N01	<b>1.0 - 10pF</b>	1.0, 1.2, 1.5, 1.8, 2.0, 2.2, 2.4, 2.7, 3.0, 3.3, 3.9, 4.7, 5.6, 6.8, 8.2, 10pF
DKD0708N02	<b>10 - 100pF</b>	10, 12, 15, 18, 20, 22, 24, 27, 30, 33, 39, 47, 56, 68, 82, 100pF
DKD0805N01	<b>0.1 - 2.0pF</b>	0.1, 0.2, 0.3, 0.4, 0.5, 0.6, 0.7, 0.8, 0.9, 1.0, 1.2, 1.5, 1.6, 1.8, 2.0pF
DKD0805N02	<b>1.0 - 10pF</b>	1.0, 1.2, 1.5, 1.8, 2.0, 2.2, 2.4, 2.7, 3.0, 3.3, 3.9, 4.7, 5.6, 6.8, 8.2, 10pF
DKD0805N03	<b>10 - 100pF</b>	10, 12, 15, 18, 20, 22, 24, 27, 30, 33, 39, 47, 56, 68, 82, 100pF
DKD0805N04	<b>10 - 220pF</b>	10, 15, 18, 20, 24, 27, 30, 39, 47, 56, 68, 82, 100, 120, 150, 180, 220pF
DKD1111N01	<b>1.0 - 10pF</b>	1.0, 1.2, 1.5, 1.8, 2.0, 2.2, 2.4, 2.7, 3.0, 3.3, 3.9, 4.7, 5.6, 6.8, 8.2, 10pF
DKD1111N02	<b>10 - 100pF</b>	10, 12, 15, 18, 20, 22, 24, 27, 30, 33, 39, 47, 56, 68, 82, 100pF
DKD1111N03	<b>100 - 1000pF</b>	100, 120, 150, 180, 200, 220, 240, 270, 300, 330, 390, 470, 560, 680, 820, 1000pF

### ≠ Custom Kits

According to the customer's demand, PPI can provide many kinds of tool kits for engineers to design and debug the circuit. All our products satisfy the requirement of RoHS instruction.

Passive Plus will develop a custom kit using the engineer's specific requirements for the engineer's projects (case size, temperature coefficient, value range, tolerances, voltages, and quantities per value). Once these requirements are determined, PPI will then provide customer with a price. Please contact PPI directly to start this process.

All kits are RoHS Compliant.







**≠ Product Features**

- High Q
- High Power
- Low ESR/ESL
- Low Noise
- High Self-Resonance
- Ultra Stable Performance
- Capacitance Range:  
470pF to 10000pF
- Working Voltage: 50V

**≠ Product Applications**

**Typical Functional Applications:**


- Tuning • Bypass • Coupling
- Feedback • D.C. Blocking
- Impedance Matching

**Typical Circuit Applications:**

- UHF/Microwave RF Power Amplifiers
- Mixers • Oscillators • Filter Networks
- Low Noise Amplifiers • Timing Circuits and Delay Lines




**≠ Part Numbering**



**≠ Capacitor Dimensions** Unit: inch (mm)

Length	Width	Thickness	Overlap
Lc	Wc	Tc	B
0.055	0.055 ± 0.010	0.057	0.014 ± 0.006
(1.40	(1.40 ± 0.25)	(1.45 max)	(0.356 ± 0.152)
+0.015 -0.010 +0.38 -0.25)			






**≠ Capacitance Tolerance Codes**

Code	K	M
Tol.	±10%	±20%

**≠ Termination Types**

Termination Code	Termination
<b>W</b>	100% Tin Solder over Nickel Barrier
<b>L</b>	90%Tin/10%Lead Solder over Nickel Barrier
<b>P</b> (Non-Magnetic) 	100% Tin Solder over Copper Barrier
<b>C</b>	100% Silver Solder over Palladium Barrier

Note: "Non-Magnetic" means no magnetic materials.

**≠ 0505X Capacitance Values**

Special capacitances, tolerances and WVDC are available. Please contact PPI.

Cap. pF	Cap Code	Tol.	Rated WVDC	Cap. pF	Cap Code	Tol.	Rated WVDC	Cap. pF	Cap Code	Tol.	Rated WVDC
470	471			1500	152			4700	472		
560	561			1800	182			5000	502		
680	681	K,M	50V	2200	222	K,M	50V	5600	562	K,M	50V
820	821			2700	272			6800	682		
1000	102			3300	332			8200	822		
1200	122			3900	392			10000	103		

### ⚡ Electrical Specifications


Operating Temperature Range	-55°C to +125°C
Insulation Resistance (IR)	Insulation Resistance @ +25°C > 1000ΩF Insulation Resistance @ +125°C > 100ΩF
Temperature Voltage Coefficient	+15/-25% ΔC (-55°C to +125°C)
Dielectric Withstanding Voltage (DWV)	2.5x WVDC, 5 seconds
Max Dissipation Factor	0.025 (2.5%) max
Test Parameters	1kHz, 1.0 VRMS, 25°C

### ⚡ Recommended Land Pattern Dimensions

Regarding Landing Patterns, please refer to IPC-7351B (table 3-5, 3-6).

### ⚡ Tape & Reel Specifications

Orientation	Measurement Unit	W	P0	P1	T	F	Min. Qty per Reel	Std. Qty per Reel	Tape Material
H	in.	0.32	0.16	0.16	0.01	0.14	500	4000	Plastic
	mm	8.00	4.00	4.00	0.30	3.50			



A<sub>0</sub>B<sub>0</sub>K<sub>0</sub>

- Determined by component size. Typical clearance between the cavity and the component is: .50 (.002) min to .65 (.026) max for 12mm tape.
- The component cannot rotate more than 20° within the determined cavity.



**≠ Product Features**

- High Q
- High Power
- Low ESR/ESL
- Low Noise
- High Self-Resonance
- Ultra Stable Performance
- Capacitance Range:  
470pF to 10nF
- Working Voltage: 50V

**≠ Product Applications**

**Typical Functional Applications:**


- Tuning • Bypass • Coupling
- Feedback • D.C. Blocking
- Impedance Matching

**Typical Circuit Applications:**

- UHF/Microwave RF Power Amplifiers
- Mixers • Oscillators • Filter Networks
- Low Noise Amplifiers • Timing Circuits and Delay Lines




**≠ Part Numbering**



**≠ Capacitor Dimensions** Unit: inch (mm)

Length	Width	Thickness	Overlap
Lc	Wc	Tc	B
0.11	0.110 ± 0.015	0.102 max	0.020 ± 0.010
(2.79	(2.79 ± 0.38)	(2.59 max)	(0.508 ± 0.250)
+0.025 -0.010 +0.64 -0.25)			








≠ Capacitance Tolerance Codes

Code	K	M
Tol.	±10%	±20%

≠ Termination Types

Termination Code	Termination
W	100% Tin Solder over Nickel Barrier
L	90%Tin/10%Lead Solder over Nickel Barrier
P (Non-Magnetic) 	100% Tin Solder over Copper Barrier
C	100% Silver Solder over Palladium Barrier

Note: "Non-Magnetic" means no magnetic materials.

≠ 1111X Capacitance Values

Special capacitances, tolerances and WVDC are available. Please contact PPI.

Cap. pF	Cap Code	Tol.	Rated WVDC	Cap. pF	Cap Code	Tol.	Rated WVDC	Cap. pF	Cap Code	Tol.	Rated WVDC
4700	472	K,M	50V	15000	153	K,M	50V	47000	473	K,M	50V
5600	562			18000	183			50000	503		
6800	682			22000	223			56000	563		
8200	822			27000	273			68000	683		
10000	103			33000	333			82000	823		
12000	123			39000	393			100000	104		

### ≠ Electrical Specifications


Operating Temperature Range	-55°C to +125°C
Insulation Resistance (IR)	Insulation Resistance @ +25°C > 1000ΩF Insulation Resistance @ +125°C > 100ΩF
Temperature Voltage Coefficient	+15/-25% ΔC (-55°C to +125°C)
Dielectric Withstanding Voltage (DWV)	2.5x WVDC, 5 seconds
Max Dissipation Factor	0.025 (2.5%) max
Test Parameters	1kHz, 1.0 VRMS, 25°C

### ≠ Recommended Land Pattern Dimensions

Regarding Landing Patterns, please refer to IPC-7351B (table 3-5, 3-6).

### ≠ Tape & Reel Specifications (mm)

Orientation	Measurement Unit	W	P0	P1	T	F	Min. Qty per Reel	Std. Qty per Reel	Tape Material
H	in.	0.32	0.16	0.16	0.01	0.14	500	2000	Plastic
	mm	8.00	4.00	4.00	0.30	3.50			



A<sub>0</sub>B<sub>0</sub>K<sub>0</sub>

- Determined by component size. Typical clearance between the cavity and the component is: .50 (.002) min to .65 (.026) max for 12mm tape.
- The component cannot rotate more than 20° within the determined cavity.



**≠ Product Features**

- High Q
- High RF Current/Voltage
- Ultra Stable Performance
- Capacitance Range:  
10nF to 1μF
- Working Voltage: 300V

**≠ Product Applications**

**Typical Functional Applications:**


- Tuning • Bypass • Coupling
- D.C. Blocking • Impedance Matching

**Typical Circuit Applications**

- UHF/Microwave RF Power Amplifiers
- Antenna Tuning • Plasma Chambers
- Medical Equipment




**≠ Part Numbering**



**≠ Capacitor Dimensions** Unit: inch  
(mm)

Length	Width	Thickness	Overlap
Lc	Wc	Tc	B
0.230	0.250 ± 0.015	0.165 max	0.030 ± 0.015
(5.84	(6.35 ± 0.38)	(4.19 max)	(0.762 ± 0.380)
+0.020 -0.012 )			
+0.51 -0.30			






**≠ Capacitance Tolerance Codes**

Code	K	M
Tol.	±10%	±20%

**≠ Voltage Codes**

Voltage	Code
100V	101
150V	151
200V	201
250V	251
300V	301

**≠ Termination Types**

Termination Code	Termination
W	100% Tin Solder over Nickel Barrier
L	90%Tin/10%Lead Solder over Nickel Barrier
P (Non-Magnetic) 	100% Tin Solder over Copper Barrier
C	100% Silver Solder over Palladium Barrier

Note: "Non-Magnetic" means no magnetic materials.

**≠ 2225X Capacitance Values**

Special capacitances, tolerances and WVDC are available. Please contact PPI.

Cap. uF	Cap Code	Tol.	Rated WVDC	Cap. uF	Cap Code	Tol.	Rated WVDC	Cap. uF	Cap Code	Tol.	Rated WVDC
0.010	103	K,M	300V	0.082	823	K,M	200V	0.560	564	K,M	150V
0.012	123			0.100	104			0.680	684		
0.015	153			0.120	124			0.820	824	K,M	100V
0.022	223			0.150	154			1.000	105		
0.033	333	K,M	250V	0.220	224	K,M	150V				
0.047	473			0.330	334						
0.068	683			0.470	474						

### ≠ Electrical Specifications


Operating Temperature Range	-55°C to +125°C
Insulation Resistance (IR)	Insulation Resistance @ +25°C > 1000ΩF Insulation Resistance @ +125°C > 100ΩF
Temperature Voltage Coefficient	± 15% Maximum
Dielectric Withstanding Voltage (DWV)	2.5x WVDC, 5 seconds
Max Dissipation Factor	0.025 (2.5%) max
Test Parameters	1kHz, 1.0 VRMS, 25°C

### ≠ Recommended Land Pattern Dimensions

Regarding Landing Patterns, please refer to IPC-7351B (table 3-5, 3-6).

### ≠ Tape & Reel Specifications (mm)

Orientation	Measurement Unit	W	P0	P1	T	F	Min. Qty per Reel	Std. Qty per Reel	Tape Material
H	in.	0.47	0.16	0.16	0.02	0.22	500	4000	Plastic
	mm	12.00	4.00	4.00	0.40	5.50			



A<sub>0</sub>B<sub>0</sub>K<sub>0</sub>

- Determined by component size. Typical clearance between the cavity and the component is: .50 (.002) min to .65 (.026) max for 12mm tape.
- The component cannot rotate more than 20° within the determined cavity.

## ⚡ Hand Soldering Chip Capacitors

Among the most common reasons multilayer ceramic chip capacitors (MLCCs) fail is improper hand soldering to printed circuit boards. Typically, one or more hairline cracks develop in the ceramic, defects that may even have an imperceptible effect on initial performance, but that manifest with time, circuit board flexure, or temperature excursions. Herein are a few tips, suggestions, and caveats to be aware of in performing a reliable hand soldering attachment.

**Solders.** Before selecting a solder, one should know the metallization on the chip. Starting at the component ceramic surface from which the electrodes protrude (typically < 1 mil), a contacting “termination” is applied that most often contains silver (Ag) or nickel (Ni). Over this is plated a barrier metal, typically nickel or copper (for non-magnetic applications), followed by a finishing metallization of tin (Sn) or lead (Pb)-tin. Other finishes may include palladium- silver (Pd/Ag), Ag, or gold (Au).

For finishes that include Ag, a silver bearing solder such as Sn62 is recommended to combat leaching of the component’s silver into the solder joint. Silver bearing solders also improve resistance to thermal fatigue. For finishes that include Au, a solder such as In50 is suggested to avoid gold scavenging that may cause embrittlement (which occurs when gold comprises approximately 3% or greater by weight of the solder joint). For finishes that do not contain noble metals, SN63 is often used, or Sn95.5 or Sn96 where there is a no-lead, e.g. ROHS, requirement.

**Fluxes.** An appropriate flux helps to clean the surfaces to be soldered and facilitates solder spread; it may also remove oxidation. Check with the solder manufacturer for a recommended flux. Rosin based fluxes are most common but require post solder cleaning.

Fluxes are available both separately as pastes and as internal cores within wire solder. Each form has advantages and disadvantages. Use of an external flux permits precise placement in exact quantities, but consideration must be given to the activation temperature of the flux, which will be lower than that of the solder liquidus, and the time spent at this temperature. Too long at the latter will result in boiling off the flux and reducing its effectiveness. Flux core solder is easy and convenient to use but may require more solder than desirable to have sufficient flux for good coverage.

In practice, external flux seems to work best for parts of size 0603 or 0505 and below, while flux core solder appears satisfactory for larger component sizes.

**Soldering iron.** A temperature-controlled iron of suitable wattage is strongly recommended. The iron temperature should typically be set 20-30°C above the solder liquidus temperature. Tip size is important; it should be about the same size as the part. Too small a tip (corresponding to an iron of insufficient wattage) will take too long to heat the printed circuit board land and part, while too large a tip (too high a wattage iron) may damage the board or component.


## ⚡ Soldering Procedure

The initial consideration is which end of the capacitor to solder first. The choice can generally be decided by recognizing that it is desirable to minimize the heat flowing directly through the component. Thus, it is best to start from the end that has the poorest heat conduction (equals highest thermal resistance) to a heat sink. (Were one to start from the opposite end, a good heat path would have been created through the capacitor to the heat sink when one soldered the second joint.) If it is not apparent which land has the poorer connection to a heat sink, begin with the one having the smallest area.

Follow these steps in soldering:

1. Pre-heat the substrate. Where possible, it is very desirable to gradually pre-heat the substrate, e.g. on a hotplate, to about 30°C below the solder liquidus temperature. Two steps are usually sufficient: Start the hotplate at a temperature about halfway to the desired pre-heat temperature, place the board on it and wait till the board temperature stabilizes, then increase the hotplate temperature to the desired final pre-heat value.
2. Pre-“tin” the traces. Select one of the PC board lands and clean it with isopropyl alcohol. If the solder you are using does not contain its own flux, place a small quantity of flux on the land, and a small amount of solder into the flux. (A razor may be used to cut a tiny custom preform from solid wire.) Place the iron on the printed circuit trace adjacent to the flux (but not touching) and heat the land until the solder melts into a flat, shallow pool. Remove the iron, then clean off any remaining flux with isopropyl alcohol. Repeat the procedure for the second land, then add fresh flux and a fresh solder preform (if not using flux-core solder) to each tinned land. (The preform should have sufficient mass to create a proper fillet – see step 5 – on the component.)
3. Pick up the component with either a hand tweezer or vacuum tweezer. (Stainless steel or ceramic-tipped tweezers are preferred.)
4. Place the component so that it straddles the circuit board lands, and make sure it lies flat on the board. As shown in **Fig. 1**, **Do not touch the component directly with the soldering iron.** Rather, touch the iron to the land adjacent to the capacitor until the solder begins to flow; then move the iron slowly toward the component.


Fig. 1



5. When a fillet forms, remove the iron. As shown in **Fig. 2**, solder fillets should occupy about 25-40% of the component's height, have a concave profile, and be free of peaks and voids.

6. Repeat steps 1-5 for the second joint, then let the board cool gradually to room temperature. Use isopropyl alcohol to remove any residual flux from each joint.

Fig. 2






## ≠ Wave Soldering

When sudden heat is applied to the elements, the mechanical strength of the components should decrease because remarkable temperature change can cause deformity of components inside. Also, long soldering time or high soldering temperatures, result in leaching by the external electrodes, causing poor adhesion or a reduction in capacitance value due to loss of contact between electrodes and end termination.

In order to avoid mechanical damage in the elements, preheating should be requested for both of the components and the PCB board. Preheating conditions are given in the table below. It is requested to keep the temperature gap between the soldering and the elements surface ( $\Delta T$ ) as small as possible.

When elements are submerged in solvent after mounting, be sure to maintain the temperature gap ( $\Delta T$ ) between the element and solvent within the range shown in the table below.

Do not apply the flow soldering to capacitors not listed in the table below.








Chip Capacitor	01005/0201/0402/0603/0505/0805
Preheating	$\Delta T \leq 150^\circ\text{C}$

PPI does not recommend flow soldering for its 1111P/1111C, 2225P/2225C, 3838P/3838C.

## ⚡ Soldering Iron


When sudden heat is given to the elements by soldering iron, the mechanical strength of the components should weaken because sharp temperature change can cause deformity of components inside. In order to avoid mechanical damage in the elements, preheating should be requested for both of the components and the PCB board. Preheating conditions are given in the below table. It is requested to keep the temperature gap between the soldering and the elements surface ( $\Delta T$ ) as small as possible. After the soldering, it should not be allowed to cool down suddenly.



Size	Soldering Iron	Temperature	Soldering Iron head Size	Solder
0505/0805	70W Thermostat Iron	330°C		63Sn/37Pb, 95.5Sn/3.8Ag /0.7Cu
1111		350°C		
2225		370°C		
3838		370°C		

**High-Q Low ESR Capacitor Tape & Reel Specifications**

Case Size	Orientation	Measurement Unit	W	P0	P1	T	F	Minimum Qty per Reel	Std Qty per Reel	Tape Material
0201N	H	in.	0.315	0.157	0.079	0.017	0.138	1000	15000	Paper
		mm	8.00	4.00	2.00	0.42	3.50			
0402N	H	in.	0.315	0.157	0.079	0.003	0.138	1000	10000	Paper
		mm	8.00	4.00	2.00	0.07	3.50			
0603N	H	in.	0.315	0.157	0.157	0.004	0.138	500	4000	Paper
		mm	8.00	4.00	4.00	0.10	3.50			
0708N	V	in.	0.472	0.157	0.157	0.012	0.217	500	1500	Plastic
		mm	12.00	4.00	4.00	0.30	5.50			
0805N	H	in.	0.315	0.157	0.157	0.009	0.138	500	3000	Plastic
		mm	8.00	4.00	4.00	0.22	3.50			
	V	in.	0.315	0.157	0.157	0.009	0.138	500	1000	Plastic
		mm	8.00	4.00	4.00	0.22	3.50			
1111N	H	in.	0.315	0.157	0.157	0.010	0.138	500	2000	Plastic
		mm	8.00	4.00	4.00	0.25	3.50			
	V	in.	0.472	0.157	0.157	0.016	0.217	500	1500	
		mm	12.00	4.00	4.00	0.40	5.50			
0505CP	H	in.	0.315	0.157	0.157	0.009	0.138	500	3000	Plastic
		mm	8.00	4.00	4.00	0.22	3.50			
	V	in.	0.472	0.157	0.157	0.012	0.217	500	2000	
		mm	12.00	4.00	4.00	0.30	5.50			
1111CP	H	in.	0.315	0.157	0.157	0.009	0.138	500	2000	Plastic
		mm	8.00	4.00	4.00	0.22	3.50			
	V	in.	0.315	0.157	0.157	0.009	0.138	500	1500	
		mm	8.00	4.00	4.00	0.22	3.50			
2225CP	H	in.	0.630	0.157	0.472	0.012	0.295	500	500	Plastic
		mm	16.00	4.00	12.00	0.30	7.50			
	V	in.	0.630	0.157	0.315	0.020	0.295	300	300	
		mm	16.00	4.00	8.00	0.50	7.50			
3838CP	H	in.	0.630	0.157	0.630	0.012	0.295	50	200	Plastic
		mm	16.00	4.00	16.00	0.30	7.50			
0505X	H	in.	0.315	0.157	0.157	0.012	0.138	500	4000	Plastic
		mm	8.00	4.00	4.00	0.30	3.50			
1111X	H	in.	0.315	0.157	0.157	0.012	0.138	500	2000	Plastic
		mm	8.00	4.00	4.00	0.30	3.50			
2225X	H	in.	0.472	0.157	0.157	0.016	0.217	500	500	Plastic
		mm	12.00	4.00	4.00	0.40	5.50			




$A_0B_0K_0$



- Determined by component size. Typical clearance between the cavity and the component is: .50 (.002) min to .65 (.026) max for 12mm tape.
- The component cannot rotate more than 20° within the determined cavity.

# PPI Passive Plus

RF & Microwave Components



Marking shown for illustration purposes only.  
Actual marking may differ.



Headquarters: New York, USA